

## CLOROBARP 438 BRILLANTE TINTOMETRIA



<b>Type of Product</b>	Enamel top coat based on modified chloride rubber resins
<b>Recommended use</b>	Weather-resistant finish
<b>Carta de Colores</b>	RAL K-7, NCS Selección 980, NOVA 720



### Characteristics of supply

	<b>Normativa</b>	<b>Specified</b>
Colour	UNE EN ISO 3668	See colour chart
Gloss(geometry 60°)		Gloss
Specific weight (Kg/L)	UNE EN ISO 2811-1	1.27+/-0.10
Solids by weight (%)	UNE EN ISO 3251	63% ± 5 (depending on colours)
Solids by Volume (%)	UNE 48090-82 (ISO 3233)	45% ± 3 (depending on colours)
Theoretical yield (m <sup>2</sup> /l)	UNE 48 282-94	12-13 m <sup>2</sup> /l (coat of 35 micras)
Conservation and Stability of the Container	UNE 48 083-92	9 months unopened, in original packaging. Store in a cool., dry place, away from frosts. Temperature range: 5-40°C

### Application Instructions

Application equipment	Aerographic spray and airless spray gun
Spray nozzle	The nozzle diameter and the spray fan angle will be selected on the basis of the piece to be coated
Application solvent	Reference: .9310
Recommended coat thickness	30-40 micras
Application on	Superficies imprimadas con imprimaciones alcídicas

### Drying / Polymerisation

Air drying (20°C-60% R.H.)	UNE 48301	(Touch) 1-2 hours
Drying for physical tests		15 days
Drying for chemical tests		15 days

### Remarks

- See general conditions
- For toxicological standards, consult FICHA DE SEGURIDAD.
- Apply with good air renewal.
- Do not store opened or started containers.
- Shake contents of containers before use.

*This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 06-10-2020 This sheet replaces all previous versions.*

## CLOROBARP 438 BRILLANTE TINTOMETRIA

