línea madera
Wood line / Ligne bois

Reference: .1037

NITROFOND 1035

Product Description	Solvent-based transparent nitrocellulose primer
Properties	Easy to apply Quick drying High covering power
Recommended use	Product suitable for sealing wooden joins and indoor furniture
Certificados	Certificado.de.Producto.Simbolo.de.Calidad.AIDIMA, Plantilla de informe



Technical Characteristics

	Norma	Value
Solids by weight (%)	UNE EN ISO 3251	31%+-2
Viscosity (Ford cup 4)	UNE EN ISO 2431	190+-50"
Density (Kg/L)	UNE EN ISO 2811-1	0.950+/-0.015

Mixing Characteristics

Solvent	Reference: .9140
Percentage dilution	30-40%

Application Characteristics

Application System	Aerographic and airless
Application on	Sanded wood
Recommended thickness of coat	150-180 gr/m²
Number of coats	1-2
Touch-dry	20 a 30 minutes (depending on thickness and temperature)
Surface sanding	2 - 3 hours, depending on thickness applied and ambient conditions
Sanding	5 - 6 hours, depending on thickness applied and ambient conditions

Remarks re application process

If you wish to seal the wood pores, you must sand the first undercoat before applying a second coat
After sanding and removing any trace of dust, apply the Nitrobarp quality nitrocellulose finishing coats.

Remarks

Shake contents of containers before use.
Apply with good air renewal.
Do not store opened or started containers.
For toxicological standards, consult FICHA DE SEGURIDAD.
Keep out of the reach of children.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. *02-06-2022* *This sheet replaces all previous versions.*

Oficinas centrales */ Headquarters / Siège social*
San Fernando, 116. D.P. 26300 Nájera. La Rioja. Spain
Tel. (34) 941 410 000 / Fax (34) 941 410 111 / www.barpimo.com