

POLPARQUET



Product Description

Varnish of Polyurethane and high quality based on single component and maximum performance



Technical Characteristics

Colour	Colourless (in dry film)
Appearance	Gloss
Touch-dry	30-60 minutes, depending on the thickness applied and atmospheric conditions
Repainting	After 2-6 hours. After 24 hours, sand appropriately to facilitate adherence.
Yield	10 - 12 m ² /l, coat, depending on conditions of surface
Thinner	DILUYENTE POLIURETANOS
Storage	Excellent up to 6 months in original containers, unopened, at normal temperatures and humidity.

Properties

Easy to apply
Filling power
Maximum yield
High hardness and balanced elasticity
Resistant to abrasion, to wear, to washing, to cleaning products and to alkalines
Finish adherent, hard-wearing, fine and decorative

Applications

Suitable for sealing and finish on wooden flooring indoors.

Method of Use

Apply well ventilated and in thin, even, well-spread coats
A round brush, brush and occasionally with spray gun: adjust viscosity with DILUYENTE POLIURETANOS

Preparation of surfaces

On without varnishing surfaces: Clean, sandpaper and eliminate dust, grease, oil, wax, small imperfections, etc.
On on worn, previously varnished or painted wood and worn surfaces: Eliminate varnish in bad conditions and proceed as before
Apply the first coat diluted, the second and third coats slightly diluted or undiluted., lightly sand between coats to facilitate absorption and improve the finish

Other data

Packaging	0.375L, 0.750L, 4L, 20L
VOCS GR/L	485.453

Remarks

Do not leave opened containers, started or diluted; their stability will be somewhat affected.
Do not dilute with non-recommended diluents
Apply with good air renewal.

For toxicological standards, consult FICHA DE SEGURIDAD.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 07-11-2013 This sheet replaces all previous versions.