

URKIFAST

2K Universal Polyester Putty



DESCRIPTION

High Quality Polyester Putty designed for its use in body shops to correct defects and fill cracks or dents.

It stands out for its adherence, filling power, flexibility and easy sanding. Bonding on sheet steel, electro-galvanized and galvanized.

COLORS

URKIFAST	7035
----------	------

HARDENERS

The use of an electronic scale is recommended. Mix homogeneously to avoid the formation of air bubbles.

Hardener	Percentage	Temperature
BPO	3%	5-10°C
BPO	2%	10-20°C
BPO	1%	>20°C

Note: Adding more hardener is not recommended in order to prevent bleedings in the paint.

SURFACE PREPARATION

The surface to be repaired must be free of rust and grease, for which we recommend previous sanding (P80-P120). On electro-zinc plating better use StarBrite.

Do not use this putty on wash-primer or phosphochromatic primers. If the original paint is thermoplastic acrylic, bare metal must be reached.

For greater substrate protection, especially in steel, use first a primer from BESA's product line such as F-286/2.

Recoatable with any Acrylic or Epoxy finish system once sealed, preferably with a 2K filler from the BESA product line.

USE



Application: By spatula.

The hardener mixture can be carried out on the same spatula, homogenizing it well before applying.

When a deep filling is required, apply several layers, letting them dry at each time during the process. Sanding at each stage is recommended in order to obtain better adhesion between the coats.

APPLICATION



	BPO
 Mixing ratio Weight	100:1-3 P
 Pot-life	3-5'
 Spatula Number of coats Total thickness	Avoid air bubble formation during its application. Vary depending on the depth of the repair. 1000-3000 µm
 Drying Time 20°C IR Medium wave	30' 5'
 Sanding	P80-P180

MIXING RATIOS



Recommended mixes	100 g	250 g
BPO mix 3%	3	7.5
BPO mix 2%	2	5
BPO mix 1%	1	2.5

SAFETY INSTRUCTIONS

The use of appropriate personal protective equipment is recommended during application, to prevent the irritation of the respiratory tract, skin and eyes. For professional use only.

STORAGE

Keep in a tightly covered container, in a dry and ventilated place, avoiding direct exposure to sunlight. Temperature above 5°C is recommended, between 15 and 30°C optimal.

VOC

The VOC content of URKIFAST is a maximum of 250 g/l in compliance with European standard 2004/42/CE IIB(B) (250) <250 g/l.

The information contained in this Technical Specification Sheet is based on the knowledge and experience of the BESA technical department, and with it it's intended to advice and inform, being the responsibility of the user to take the necessary measures to guarantee the intended purpose of the product. **FOR PROFESSIONAL USE ONLY.**
