

ColorCan gives an excellent UV resistant finish that provides good gloss levels and opacity. Drying times are fast, allowing quicker handling of articles. The product will adhere directly onto Mild Steel and other ferrous substrates.

Hundreds of colours available including a selection of RAL, NCS, Pantone, BS, F&B, Dulux, Colortrend etc

Features and benefits

- **High-quality Acrylic finish**
- **Excellent durability - resistance against weathering and UV influences**
- **Very fast drying - touch dry in 10 minutes**
- **Outstanding opacity - less coats and time required**
- **Lasting gloss level**

Physical and chemical data

Basis of binder	Acrylic
Colour	Various
Coverage	1.5 - 2m²
Temperature resistance	Up to 110°C
Storage stability	10 years if appropriate storage provided - 10°-25°C, humidity max. 60%)
Size	500ml aerosol
VOC content	658g/lit
Drying times @ 20°C	
Touch Dry	5 - 10 minutes
Dry to Handle	10 - 20 minutes
Re-coat	After 20 minutes

Application guide

- **Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means.**
- **Prime or spot prime with the recommended ProXL Primer.**
- **Sand intact coatings to provide a proper key for adhesion.**
- **Shake aerosol for at least two minute after the agitator ball is free.**
- **Shake aerosol during use**
- **Apply at a distance of 25 cm from the treatment area**
- **Apply several coats allowing for a 5 - 10 mins flash off between coats**
- **After use turn aerosol upside down and empty valve for 2 - 3 seconds**

Suitable substrates

- **Mild Steel**
- **UPVC**

Environmentally sound

The products supplied by ProXL are 100% free of heavy metals and the caps and packaging are made of recyclable material.

Disposal

Completely emptied cans should be put in recycling skips or appropriate container. Cans which are not empty should be disposed off as special refuse.

This application and technical information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively is the responsibility of the user.

