

TECHNICAL DATA SHEET

AQUALAC GLOSS

Code: 10.300

MARCH 2015

DESCRIPTION

Waterborne enamel based on quick drying acrylic resins, giving permanent whiteness and excellent exterior performance. Low odor & very fast drying. Developed to have many characteristics of an alkyd enamel. Provides outstanding hardness, brushability, adhesion, and scrubability. Features:

- Excellent adhesion, flow and leveling.
- Excellent hiding power and coverage.
- Hardness & Splatter resistant
- Interior/Exterior Formula

USE: INTERIOR - EXTERIOR

AQUALAC provides unsurpassed hiding on interior trim and cabinets, and exterior trim and doors. It is recommended for use on properly prepared and primed interior wood, plaster and drywall and exterior doors and trim, masonry and metal.

SURFACE PREPARATION

Wood:

Surface must be clean, dry, grease-free and sanded. Primer the inside using Synthetic Sealer primer and the exterior with Fondo Protector.

Iron & Steel:

Primer with the right antioxidant product after grease and rust have been removed.

Aluminum and galvanized surfaces

Primer after cleaning with Waterprim primer

Cimen, pladur, plaster

Surface must be clean. Primer with JUNORAL N-5.

APPLICATION

Apply with a high quality brush, roller or by spray equipment.

Spray equipment must be handled with due care and in accordance with manufacturer's recommendation.

Where necessary, apply a second coat. Product is ready to use and no thinning is usually required. May be diluted with 5-10% water.

Well preserved previously coated surfaces can be repainted after washing and sanding the surface to completely remove shine. For paint in poor condition, remove completely, clean and apply new paint. Clean-up: With water.

Dying: Using Colorante Junoral or Colorante Universal not exceeding 2%.

OBSERVATIONS

Stir thoroughly before and occasionally during use.

Water based paints are extremely sensible to weather and surfaces conditions.

To obtain good results, it is essential to apply under dry and tempered conditions, (Between 10 and 25° C). Surfaces must be perfectly clean, rustfree, dust and grease-free, without any pollutant that can affect the paint's performance.

USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.

APPLICATION RECOMMENDATIONS

Surfaces to be coated must be dry, clean, sound, and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, concrete curing agents and bond breakers, chalk, efflorescence, mildew, rust, product fines, and dust. Remove loose paint, chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Putty/plaster all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Feather back all rough edges to sound surface by sanding. Prime all bare and porous substrates with an appropriate primer. Follow recommended application temperature and the drying times between coats (20°C, relative humidity 65%). Calculate necessary quantity by taking into account the m², porosity and support texture. Store the remaining product in a dry and well-ventilated place.

The information contained in this data sheet may vary and must be updated. Please visit www.juno.es or consult with your nearest JUNO representative who will provide you with the most recent date sheet. Our technical instructions and advice whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, they must only be interpreted as indications WITHOUT LIABILITY even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the intended procedures and purposes. The application, use and processing of the products supplied by JUNO are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.

Finish: Gloss

Color: White, other colors under request

Viscosity: 20 minimum S/FR1007 poises

Density: 1,22 +/- 0,05 s/FR 1001

Drying time: 1 hour to the touch

Repaint: Minimum 24 hours.

Maximum: 8 days

Flashpoint: Non flammable.

Performance : 10 m² / L/ coat

Solvent: Water

VOC's content: Maximum 70 g/l

Reaction to Fire: B-s1,d0 (UNE 13501-1:2007)

CLEANING

Clean all exposed skin areas and application tools with warm, soapy water as soon as possible after application.

Clean spray and stains immediately with soapy water or with an adequate solvent.

Clean tools after use (brushes, rollers, equipment etc.) and let dry before storage.

Consult your town council about appropriate recycling methods for container, waste and excess paint, in accordance with the existing legislation and environmental protection principles.

SHIPPING



Packaging: 0,75/4 liters
Shipping Weight:
Units per pallet: 525/150



Freight Classification:
 Paint or paint related material



Transport Information
 No restriction for transport (ADR/RID, IMDG, IATA)

