

PINTURAS JUNO

DATA SHEET

JUNOPLUS GLOSS Enamel

CODE: 4.2--

DESCRIPTION

An alkyd resin based fire-resistant gloss enamel.

USAGE: INDOOR - OUTDOOR

A general purpose finishing enamel, aimed to protect and decorate suitably primed wood, masonry or metal surfaces.

CHARACTERISTICS

• Finish	Gloss
• Colour	See colour chart
• Viscosity	Min 100" S/FR1002
• Density	1.10-1.45 g/cc S/FR1001
• Drying time	To the touch: 8 hours Second coat: Minimum: 24 hours Maximum: 8 days
• Diluent	D-16 or White Spirit
• Solids in volume:	(46 +/- 2) % . Theoretical
• Reaction to fire:	M-1 UNE 23727-90
• Coverage	11m ² / Lt (40 dry microns)
• VOC content	Maximum: 400 g/l

SURFACE PREPARATION

WOOD

It must be clean and dry, grease-free and sanded. Prime indoor with **Hangers Synthetic Sealer**, and outdoor with **Wood Preserver**. Sand down between coatings.

IRON AND STEEL

Remove grease and rust, and prime with **Metalex Red Lead** or an appropriate antioxidant agent.

ALUMINIUM & GALVANISED SURFACES

Once cleaned, prime with **Multipurpose Primer**.

Previously painted surfaces, when in good condition, can be painted directly once washed and lightly sanded in order to fully remove the gloss. If the paint is in a poor condition, it must be thoroughly removed. Clean up and treat as new.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32

INTERNET:www.juno.es - E-MAIL: infoweb@juno.es

APPLICATION INSTRUCTIONS

Use a suitable brush or enamel roller directly and spread the paint evenly. For spray painting, dilute with 10 - 15 % of **D-17**, **not exceeding 30- 35 dry microns per layer in both cases**.

Temperature: The application temperature must be between +5°C and + 35°C.

APPLICATION CONDITIONS

Temperature: The application temperature must be between +5°C and + 35°C.

When less opaque colours are used, such as reds, yellows or oranges, a similar colour good coverage undercoat it is recommended.

DYING

Use **Juno Universal Colorant** at ratios not exceeding 2 %.

CLEANING

D-16 Solvent or Universal Solvent

REPAINTING

With alkyd resin based enamels thinned with **White Spirit or Turpentine**.

OBSERVATIONS

Stir the recipient contents thoroughly until evenly mixed.

Add the required amount of solvent while stirring.

PACKAGING

Lithographed metal container. Sizes: **0.750 and 4 litres**

Date: January 2007/Revision: 6

N.B.: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, it must only be construed as an indication **WITHOUT LIABILITY** even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the procedures and purposes intended. The application, use and processing of the products supplied by us are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32

INTERNET:www.juno.es - E-MAIL: infoweb@juno.es