

## QUICK DRY UNDERCOAT

**Dulux Trade** Quick Dry Undercoat is part 1 of an advanced 2 part water-based, high gloss system, with excellent opacity and coverage. It is specifically designed to provide the best top-coat finish with **Dulux Trade** Quick Dry Gloss, but can be used on all interior wood and metal.

### KEY BENEFITS

- Excellent Coverage
- Advanced Water Based Technology
- Perfect for **Dulux Trade** Quick Dry Gloss

### PRODUCT INFORMATION

#### Typical Use

Suitable for on interior wood and metal surfaces.

#### Pack Size

1L, 2.5L and 5L.

#### Colour Range

See appropriate **Dulux Trade** colour literature or visit [duluxtrade.co.uk](http://duluxtrade.co.uk).

#### Film Properties

*Film thickness will be dependent on the coverage achieved.*

**Wet:** 75-85 microns.

**Dry:** 25-30 microns.

#### Composition (nominal)

**Pigment:** Lightfast pigments.

**Binder:** Acrylic Copolymer Emulsion.

**Solvent:** Water.

#### Volume Solids

Typical 34% (nominal).

### SURFACE PREPARATION

To get the best results, ensure surfaces to be painted are sound, clean and dry.

Thoroughly rub down previously painted surfaces, using 'wet flattening' methods where possible, then wipe off with a damp, lint free cloth. Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead.

Treat knots with an appropriate knotting solution. Any surface defects should be filled with the appropriated **Polycell Trade Polyfilla**.

When applying water-based paints to surfaces previously decorated with a conventional solvent-based paint, very thorough surface preparation will be necessary.

### SYSTEMS INFORMATION

STIR THOROUGHLY BEFORE USE. Apply 1 or 2 coats of **Dulux Trade** Quick Dry Undercoat, as required, followed by 1 or 2 coats of **Dulux Trade** Quick Dry Gloss. Where a strong colour change is involved, 2 coats will be required. Newly painted doors and windows should not be closed (tightly) until the paint is fully dry.

### APPLICATION METHOD

Apply by brush, roller or spray. For best results use a good quality synthetic (nylon polyester) brush, designed for use with water-based paints.

To get the best with the **Dulux Trade** Quick Dry Undercoat, lightly dampen both a synthetic brush and the surface before application to increase flow out.

As with other water-based paints, do not apply at temperatures below 8°C (as recommended by British Standards BS 6150).

#### Practical Coverage

A guide to the practical coverage which can be achieved is up to 10m<sup>2</sup> per litre.

#### Thinning

Thinning is not usually necessary, but if required add up to 1 part clean water to 20 parts paint.

#### Spray Recommendations

**Conventional Spray:** Satisfactory through most types of conventional spray equipment.

## QUICK DRY UNDERCOAT

**Airless Spray:** A typical recommendation for airless spray application is a minimum working pressure on paint of 138 bars (2000 lb/sq in) with a spray tip size of 0.43mm (17 thou) and a spray tip angle of 60°.

### Drying Times

*Single coat at standard thickness:*

**Touch Dry:** Dependent on temperature and humidity.

**Recoat:** 4-5 hours.

### Cleaning Up

After use, remove as much product as possible from equipment before cleaning with water.

When this paint container is empty please ask your stockist about recycling. If you have leftover paint, please dispose of it responsibly and consider donating it to **Community RePaint**. Find out more at [duluxtrade.co.uk/pp](http://duluxtrade.co.uk/pp).

### Transportation & Storage

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

### VOC

EU limit value for this product (cat.: A/d): 130g/l (2010). This product contains max. 90g/l VOC. VOC Content: Medium (8-24.99%).

## FURTHER SUPPORT

If you need further support, please contact the **AkzoNobel** Technical Advice Centre on [0333 222 70 70](tel:03332227070).

***Always read full Health, Safety & Environmental Information on can before use.***

Safety datasheet (SDS 552) is available free on request by telephoning the **AkzoNobel** Technical Advice Centre or by visiting [duluxtrade.co.uk](http://duluxtrade.co.uk).

AkzoNobel, the AkzoNobel logo, the Flourish logo, Dulux Trade, Polycell, Polyfilla, Community RePaint and the Planet Possible logo are trademarks of the AkzoNobel group. © AkzoNobel 2014.