

LACAPOL FENIX BASE TINTOMETRIA



Product Description	BASE PRODUCT FOR MAKING COLOURS IN TINTOMETRY
Properties	Alkyd nature High covering power Silky feel
Recommended use	Product to use for varnishing woodwork and indoor furniture
Certificados	Certificado.de.Producto.Simbolo.de.Calidad.AIDIMA, Fondipol.250.Blanco.y.Lacapol.Fenix.pdf



Technical Characteristics

	Norma	Value
Solids by weight (%)	UNE EN ISO 3251	58% ± 2
Viscosity (Ford cup 4)	UNE EN ISO 2431	80" ± 10
Density (Kg/L)	UNE EN ISO 2811-1	1.260+/-0.020
Colour		Wide range of colours
Shine (60° angle)	UNE EN ISO 2813	Matt and semi matt

Mixing Characteristics

Hardener		HARDENER N.245 / HARDENER N.296
Mix Proportion (% Volume)		50%
Mix Solids (%)	UNE EN ISO 3251	50% ± 2
Viscosity of mix (Ford cup 4)	UNE EN ISO 2431	35" ± 5
Pot life mixture	UNE EN ISO 9514	4 to 5 hours at 20°C
Solvent		Reference: .9130

Application Characteristics

Application System	Aerographic and airless
Application on	Pigmented polyurethane primers or pigmented polyacrylic perfectly sanded and dust removed
Recommended thickness of coat	120-130 gr/m ²
Dry to dust	15 a 30 minutes (depending on thickness and temperature)
Touch-dry	30 a 50 minutes (depending on thickness and temperature)
Total hardening	1 days
Repainted	For second coat after 8 - 10 hours

Remarks re application process

Soft colours: N.245 hardener

Intense colours: N.296 hardener.

In the case of an increase in viscosity after the application, reduce with .9130

If the ambient temperature is high, use .9020 to dilute

If repainting is required after applying the first topcoat, gently sand to achieve adherence between coats

Remarks

Shake contents of containers before use.
Apply with good air renewal.
Do not store opened or started containers.
Maximum stability of hardener is less than 6 months at 20°C.
For toxicological standards, consult FICHA DE SEGURIDAD.
Keep out of the reach of children.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 29-03-2011 This sheet replaces all previous versions.