

PINTURA EPOXI SUELOS AL DISOLVENTE



Product Description

Paint industrial floors, indoors and of maximum quality based on special Epoxy resins and highly colour fast pigments

Carta de Colores

[Carta de colores Pinturas para Suelos](#)



Technical Characteristics

Colour	Chrome green, english red, ral 7038 grey and barpicolor II system
Appearance	Gloss
Touch-dry	5 - 6 hours, depending on thickness applied and ambient conditions
Repainting	After 12-24 hours
Yield	7-9 m ² /l, per coat, depending on the state and type of surface
Thinner	BARPISOL EPK 280
Storage	Excellent up to 6 months in original containers, unopened, at normal temperatures and humidity.

Properties

Easy to apply
 Good covering power.
 Filling power
 High hardness and balanced elasticity
 Finish adherent
 Resistant to abrasion, to wear, mopping, oil spills, mineral oil, other chemical agents and dirt in general
 Eliminates the formation of dust on the floor, improves surface hardness, avoids erosion and wear and tear making the floor easier to clean and more decorative.

Applications

Suitable for concrete floors, cement mortar and other derivatives.
 Suitable for indoors and garages, workshops, wine cellars, industrial units, factories, car parks.

Method of Use

Stir the contents of the pot well
 Prepare the amount to be used
 Shake until completely mixed. (mixing machine)
 Supplied in two containers, Component A and Component B.
 Mix proportion (by volume): 3 parts of A" and 1 parts of "B".
 Allow to stand for 30 minutes.
 Mixture pot life 8-10 hours at 20 °C.
 Apply well ventilated and in thin, even, well-spread coats
 Application at: Round brush and roller

Preparation of surfaces

Surfaces should be sanded, clean, dry and free from dust, grease, oil and moisture.
 Clean floor, dry and well hardened (28 days)
 Residual floor humidity at 6%.

Preferably rough to improve adherence.

On unpainted surfaces: Apply 2 or 3 coats as used (the first coat slightly diluted), 2nd and 3rd coats diluted or as used for a finish

On with old paintwork surfaces: Remove damaged paintwork and proceed as for unpainted surfaces

Recommendations before application

Do not apply in temperatures below 12°C.

Relative ambient humidity below 80%

Surface temperature higher than 8°C

Other data

Packaging 4L (3+1), 16L (12+4)

Remarks

Shake contents of containers before use.

For toxicological standards, consult FICHA DE SEGURIDAD.

Do not store opened or started containers.

Apply with good air renewal.

Maximum stability of hardener is less than 6 months at 20°C.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 26-01-2016 This sheet replaces all previous versions.