

## NITROBARP 280 BLANCO



<b>Product Description</b>	White, solvent based nitrocellulose top coat
<b>Properties</b>	High covering power Quick drying
<b>Recommended use</b>	Lacquer for indoor furniture.
<b>Certificados</b>	<a href="#">Certificado.de.Producto.Simbolo.de.Calidad.AIDIMA</a> , <a href="#">Plantilla de informe</a>



### Technical Characteristics

	Norma	Value
Solids by weight (%)	UNE EN ISO 3251	28% ± 2
Viscosity (Ford cup 4)	UNE EN ISO 2431	150" ± 15
Density (Kg/L)	UNE EN ISO 2811-1	1.010+/-0.020
Shine (60° angle)	UNE EN ISO 2813	Matt, satin and gloss

### Mixing Characteristics

Solvent	Reference: .9140
---------	------------------

### Application Characteristics

Application System	Aerographic, airless and curtain
Application on	Nitrocellulose or polyurethane undercoats, perfectly sanded and removing dust
Recommended thickness of coat	120-130 gr/m <sup>2</sup>
Dry to dust	10 a 20 minutes (depending on thickness and temperature)
Touch-dry	20 a 40 minutes (depending on thickness and temperature)
Can be handled	3 - 4 hours, depending on thickness applied and ambient conditions
Total hardening	1 days
Repainted	For second coat after 5 - 6 hours

### Remarks re application process

If repainting is required after applying the first topcoat, gently sand to achieve adherence between coats  
In the case of moisture or high ambient temperature during application, use BARPISOL RT 61.

### Remarks

Shake contents of containers before use.  
Apply with good air renewal.  
Do not store opened or started containers.  
For toxicological standards, consult FICHA DE SEGURIDAD.  
Keep out of the reach of children.

*This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 22-12-2010 This sheet replaces all previous versions.*

