

## MOTIP Wheel Paint

Ord.-no.: look at ordering information

## Technical Information



Renew and repair steel and other light metal rims and hubcaps of your car with MOTIP Wheel Paint. Wheel Paint is a fast-drying acrylic paint with lasting gloss offering good coverage, excellent adhesion and good surface hardness. It is resistant to petrol, chemicals, the weather and is UV-resistant and non-fading. Wheel Paint is resistant to wear and scratches.

### Quality & properties

- Non-fading and UV-resistant
- Fast drying
- Good coverage
- Resistant to petrol, chemicals and weather influences
- Good surface hardness
- Lasting gloss
- Wear-resistant and scratch free
- Excellent adhesion

### Physical & chemical data

- Base: Acrylic resin
- Colourname:
  - ◊ Steelwheel
  - ◊ Black
  - ◊ White
  - ◊ Gold
  - ◊ Silver
- Degree of gloss:
  - ◊ gloss, >75 GU
  - ◊ mat, 10 ±2 GU
- Efficiency: 500 ML – 4-5 m<sup>2</sup>
- Dry to touch: 10 -20 min
- Dust dry: 5-10 min
- Completely dry: 120 min
- Overcoatable: 120 min
- Surfaces: Steel and light metal rims and hubcaps.
- Minimum Working Temperature: 10 °C
- Maximum Working Temperature: 25 °C
- Vapour pressure:
  - ◊ 3500/20 bar
  - ◊ 4000/20 bar
  - ◊ 13/20 bar
- Flash point:
  - ◊ n.a.
  - ◊ 27 °C
- Storage stability:
  - ◊ 10 years
  - ◊ 5 years
- Content:
  - ◊ 500 ML
  - ◊ 12 ML

### How to use

- Before use, carefully read the directions on the packaging and act accordingly.
- Pre Treatment: The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of MoTip primer suitable for the surface. After drying, sand the base layer (grain 600).
- Treatment: The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C.
- Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.
- Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.
- In order to obtain high gloss, apply a finishing coat of MoTip acrylic clear varnish.

- After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).
- The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

**Environmentally sound**

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

**Disposal**

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

**Marking/Labeling**

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +31 (0) 561 69 44 00 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

**As of November 24, 2021** – This release replaces all eventually earlier issued versions.

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim - [info-de@european-aerosols.com](mailto:info-de@european-aerosols.com)  
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega - [info-nl@european-aerosols.com](mailto:info-nl@european-aerosols.com)