




# RUBBERcomp®

Durable coating  
**EASY to undress!**



## MASTON RUBBERcomp® LIQUID PAINT

RUBBERcomp® is a multi-purpose, air drying specialty rubber coating. It can be easily applied by spraying. It protects coated items against moisture, acids, abrasion, corrosion, and skidding /slipping, and provides a comfortable, controlled grip.

RUBBERcomp® remains flexible and stretchy over time, and will not crack or become brittle in extreme weather conditions. It has been tested and proven in temperatures from -30°C to +90°C. Easy to peel off. Around four paint layers needed for adequate film thickness.

### QUALITY AND PROPERTIES

Base: synthetic rubber polymers  
Can be applied wet-on-wet or wet-on-dry  
Forms an electric, weather and abrasion proof layer  
Remains flexible in wide temperature area  
Easy to strip simply by tearing off the rubber layer  
Degree of gloss: matt, semi-gloss or high gloss

### PHYSICAL AND CHEMICAL DATA

Smell: solvent  
Colour: see the label of the can

### APPLICATION AREAS

Metal: improved wear resistance, corrosion resistance, vibration reduction, sound damping, electrical insulation  
Wood: seals and prevents cracking.  
Glass: improves shatter-proof features  
Textiles and ropes: weatherproofs, prevents rotting and fraying.  
Plastics: forms an elastic, scratch resistant layer.  
Rubber: forms an elastic, scratch resistant layer.  
Paper and cardboard: provides a weatherproof, tear resistant layer

**EU VOC-CONTENT:** IIB (e), VOC max. 840g/L (2010), VOC 614g/L

### DRYING

Drying time (at 20°C, 50% relative air humidity):  
Dust-dry: after 20 minutes  
Dry to touch: after 40 minutes

Completely dry: after 10 hours

Final hardness: around 2 days

Recommended applying temperature +18 - +25°C. Applying in cooler temperatures may affect drying times, finish quality, and spray performance.

### INSTRUCTIONS FOR USE:

Clean the surface of oils, grease, dirt, wax and loose rust. Dilute 1L paint with 450ml thinner, margin ±5%. Mix well before use. Pneumatic paint guns use compressor pressure 2.5 bar max and nozzle 1.1 - 2.0 mm. Electric paint gun adjustment depending on type. Test always on an external panel first and adjust the spray gun starting from lowest position and increase until you are able to apply a wet, uniform coat without dripping. Spray at least four layers following separate RUBBERcomp® painting instructions / technical information sheet. Do not use any other thinner than RUBBERcomp® thinner.

Before closing the can after use, pour a little thinner on top of the paint to prevent skinning. Do not mix, close the cover.

### STORAGE STABILITY:

36 months if appropriate storage provided (=+10°- +25°C, relative air humidity of max. 60%)

### SIZES:



250 ml, 1000 ml, 3000ml Liquid  
450ml and 800ml Thinner



# RUBBERcomp® Liquid

**MASTON**

250 ml 



1 l 



Maston Oy • [www.maston.fi](http://www.maston.fi) • [maston@maston.fi](mailto:maston@maston.fi)

Teollisuustie 10, FI-02880 Veikkola, Finland, Tel. +358 20 7188 580, Fax +358 20 7188 599



Теоллисуэтиэ 10, 02880 Вейккола, Финляндия, Тел. +358 20 7188 580, Факс. +358 20 7188 599



# RUBBERcomp® Liquid

**MASTON**

3 l 



Maston Oy • [www.maston.fi](http://www.maston.fi) • [maston@maston.fi](mailto:maston@maston.fi)

Teollisuustie 10, FI-02880 Veikkola, Finland, Tel. +358 20 7188 580, Fax +358 20 7188 599  
Teollisuustie 10, 02880 Вейккола, Финляндия, Тел. +358 20 7188 580, Факс. +358 20 7188 599

