

LACAPOL IGNIFUGO BLANCO



Product Description	Twin component solvent based white polyurethane top coat Alkyd nature
Properties	Product with fireproof properties High covering power High filling power
Recommended use	Topcoat to use on furniture requiring FLAMEPROOF PROPERTIES
Certificates	Reaction to fire according to UNE-EN 13501-1:2007+A1:2010 rated B-s2,d0
Certificados	Certificado.de.Producto.Simbolo.de.Calidad.AIDIMA , Fondipol.y.lacapol.ignifugos.pdf



Technical Characteristics

	Norma	Value
Solids by weight (%)	UNE EN ISO 3251	65% ± 2
Viscosity (Ford cup 4)	UNE EN ISO 2431	85" ± 10
Density (Kg/L)	UNE EN ISO 2811-1	1.27+/-0.020
Shine (60° angle)	UNE EN ISO 2813	Matt and satin

Mixing Characteristics

Hardener		CATALIZADOR Nº 245
Mix Proportion (% Volume)		50%
Mix Solids (%)	UNE EN ISO 3251	55% ± 2
Viscosity of mix (Ford cup 4)	UNE EN ISO 2431	35" ± 5
Pot life mixture	UNE EN ISO 9514	6 to 7 hours at 20°C
Solvent		Reference: .9130

Application Characteristics

Application System	Aerographic, airless and curtain
Application on	WHITE FIREPROOF FONDIPOL A1225
Recommended thickness of coat	120-130 gr/m ²
Dry to dust	25 a 40 minutes (depending on thickness and temperature)
Touch-dry	40 a 60 minutes (depending on thickness and temperature)
Total hardening	1 days

Remarks re application process

In the case of an increase in viscosity after the application, reduce with .9130
If the ambient temperature is high, use .9020 to dilute

TO HAVE A FIREPROOF SYSTEM IT IS COMPULSORY TO FIRST APPLY WHITE FIREPROOF FONDIPOL PRIMER REF: A1225

Remarks

Shake contents of containers before use.

Apply with good air renewal.
Do not store opened or started containers.
Maximum stability of hardener is less than 6 months at 20°C.
For toxicological standards, consult FICHA DE SEGURIDAD.
Keep out of the reach of children.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 25-02-2015 This sheet replaces all previous versions.