

PROMOTOR 895
PLASTIC ADHESION PROMOTER

Edition: 021 2014/05
Cod: 7089500000.00000.021

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Adhesion promoter for many different plastic types used in the automotive market, garden furniture or any other hard plastic parts, such as PP, PUR, PS, PA, PP-EPDM, ABS, PVC, GRP, PC.

Suitable for spot repairs and small surfaces. Very easy application and good adhesion on the above mentioned plastic surfaces.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	0,87 ± 0,02
Supply viscosity at 20°C	12-14 sec. Ford nº 4
% Solids content (weight / volume)	4 % ± 1 weight/vol.
V.O.C. (g/l)	835 (Ready to use)
Type of product	Modified Chlorinated Polyolefinic
Colour	Colourless

SURFACE PREPARATION

Clean the surface with water and soap. Once the surface is dry , degrease with Thinner nº 94.

If the plastic surface is not even, it is recommended to heat the piece to make any residues of the mould release agents reach the surface for an easier cleaning.

APPLICATION INSTRUCTIONS



12-14" Spray-gun



Not needed



2-4 my



2 min.



Dry 5 min.

FEATURES OF DRY FILM

Theoretical yield (m²/l)	10 - 11 (3 my)
Gloss 60°-60°	Matt
Second layer	After 5 min

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended.

Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.