

## MOTIP Glass Fibre Putty Unfilled

Ord.-no.: 000082, 000083

### Technical Information



Fill deeper damages like holes in surfaces of steel, aluminium, wood, concrete and polyester with MOTIP 2-component Glass Fibre Putty (unfilled). Glass Fibre putty has excellent filling properties. It offers high impact resistance and may be resprayed with all paints. It is resistant to chemicals and the weather and can be applied in layers up to 2 cm in thickness.

#### Quality & properties

- Can be sanded mechanically
- Excellent filling properties
- High impact resistance
- Re-sprayable with all lacquer systems
- Resistant to chemicals and weather influences
- Excellent adhesion

#### Physical & chemical data

- Base: Polyester resin
- Colourname: Grey
- Smell: characteristic
- Degree of gloss: mat,  $10 \pm 2$  GU
- Completely dry: 60 min
- Overcoatable: 60 min
- Sandable: 30 min
- Surfaces: Steel, aluminium, wood, concrete, polyester
- Minimum Working Temperature: 10 °C
- Maximum Working Temperature: 25 °C
- Vapour pressure: 6/20 bar
- Flash point: 31 °C
- Relative density: 1.67 g/ml
- Pot life: 3-5 min
- Addition of hardener: 2.5 %
- Storage stability: 1.5 years
- Content:
  - ◊ 250 G
  - ◊ 1,00 KG

#### How to use

- Before use, carefully read the directions on the packaging and act accordingly.
- Processing temperature 15 – 25°C
- The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.
- The surface should be clean, dry and free of grease. Mix the required amount of putty with the harder. Apply in the desired layer thickness. After hardening, sandable mechanically. When desired apply a fine putty.
- The drying time depends on the ambient temperature.
- After use, directly clean the tools used. Do not store the surplus material, mixed with harder, in the can.

#### Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

#### Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

#### Marking/Labeling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +31 (0) 561 69 44 00 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim - [info-de@european-aerosols.com](mailto:info-de@european-aerosols.com)  
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega - [info-nl@european-aerosols.com](mailto:info-nl@european-aerosols.com)