

ProXL Generation20 ToughOX is a high-performance 2K polyurethane structured coating, giving a high ultimate protection for truck bed lining as well as many other industrial applications. ToughOX provides an extremely durable, impact resistant, impermeable finish. It is available in black or tintable versions.

Features and benefits

- Excellent adhesion to most surfaces
- High UV and weather resistance
- Highly flexible
- Excellent shock and scratch resistance
- Highly resistant to fuels, chemicals and oils
- Excellent water resistance
- Provides sound deadening and noise reduction
- Easy to clean

Preparation of substrates

- Clean and degrease the surface
- Remove all loose material and any rust from surface
- Sand the surface with P80-P180 grit
- Re-clean with degreaser

Recommended primer for common substrates

Substrate	No primer required	ProXL 2kEpoxy Primer or equivalent	ProXL Ultraetch 1K Primer or equivalent	ProXL Ultragrip
Original paintwork	●			
E-coat	●			
Bare steel		●	●	
Aluminium		●	●	
Galvanised		●	●	
GRP & Fibreglass				●
Plastic (Except PE)				●

Mixing guide

This product is colourless, so requires tinting prior to use.

1. Open can of ToughOX and add 125ml of a solvent based tinter of your choice, followed by one full can of hardener TOG20-H (200ml).
2. Screw on the metal cap and shake well for 2 minutes
3. Remove the cap and screw the can onto your application gun

UBS Spray Gun

Nozzle:	3.0mm (coarse texture)
Pressure:	3-4 bar (45-60 PSI)
Distance from object:	Min 40cm
Number of coats	2 coats in an even sweeping motion
Flash off between coats	10-15 minutes @ 20°C

HVLP Spray Gun

Nozzle:	1.8-2mm (fine texture) 2.5mm (coarse texture)
Pressure:	2 bar (30 PSI)
Distance from object:	Min 20cm
Number of coats	2-3 coats. 1 st coat applied as an even wet coat, 2 nd coat reduce pressure to achieve finish
Flash off between coats	10-15 minutes @ 20°C

Paint Roller

For uniform appearance, complete all rolling while product is still wet. Texture can be increased with additional rolling. To avoid trapping solvent do not over apply. Any pooled or over applied areas should be brushed.

Drying Times

Touch dry:	60 minutes @ 20°C
Through dry:	5-7 days
Baking:	30 minutes @ 60°C
IR curing:	Not recommended
Pot life:	4 hours @ 20°C

IMPORTANT: Do not stack or load heavy objects onto the painted surface until the coating is fully cured. Always adhere to the drying times above. Thicker coats will extend the final curing time.

VOC and Storage

Directive:	2004/42/IIIB (e) VOC Max. 840 g/l
VOC:	240 g/l
RFU when mixed with activator:	VOC 276 g/l

Product is recommended to be stored in cool, dry conditions in original containers between 5-27°C. The shelf life of the product is 24 months from date of manufacture in unopened containers.



DISCLAIMER OF LIABILITY

The information contained in this Technical Data Sheet is correct to the best of Alpha Coatings Limited trading as Capella Solutions Group's ("Capella") knowledge, however, you must satisfy yourselves that the Goods are suitable for your needs by way of your independent testing or other processes. Capella makes no warranty, representation, or guarantee regarding the information contained in the Technical Data Sheet or the suitability of its products and services for any particular purpose, nor does Capella assume liability arising out of the application or use of the Goods other than any liability which cannot be limited by law including but not limited to liability for: (a) death or personal injury caused by negligence; (b) fraud or fraudulent misrepresentation; and (c) breach of the terms implied by section 12 of the Sales of Goods Act 1979, in such circumstances Capella's total liability shall not exceed the cost of the Goods. Capella's total liability includes liability in contract, tort, negligence, breach of statutory duty, or otherwise. It is the Customer's responsibility to ensure that the guidance on the Technical Data Sheet is followed.