

E-750

ACCELERATOR FOR ACRYLICS-POLYURETHANES

Edition: 020 2012/09

Cod: 8000000750.00000.020

APPLICATION**"USE ONLY IN INDUSTRIAL FACILITIES"**

E-750 has been formulated to reduce drying times of 2K acrylic and poliurethane products without any loss of the paint properties. Not to be used in epoxi nature products.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	0,87 ± 0,02
V.O.C. (g/l)	863
Flash Point	21-55°C Method: closed cup
Boiling point (°C)	> 35°C
Type of product	Accelerator additive
Colour	Clear and colourless

APPLICATION INSTRUCTIONS

Add in between 1 and 3% of the total amount of paint.

Not recommended as a preventive measure. Adding more than the advised % may reduce pot life of the mixing and cause loss of gloss, worse levelling, pinholes,...

The additive must be poured onto the A component or onto the A+B mixing just before the application. Not advised onto the hardener as there may be stability problems in the part of the hardener not used.

FEATURES OF DRY FILM

-	Accelerating effects.
---	-----------------------

COMPOSITION

Type of product	Aromatic hydrocarbons/ Organic tin salt
-----------------	---

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.

Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.