

URKI-RAPID 70

QUICK DRYING SEMIGLOSS SINGLE COAT

URKI-SYSTEM

CONVERTER: 6005 / CONV U-RAPID 70
RELATION PASTE / CONV.: 15/85 weight (12/88 V.)

Edition: 021 2012/10

Cod: 6900500000.00000.021

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Suitable for agricultural machinery and for public works, cranes, construction material, scaffolding, containers, etc. It presents a semiglossy aspect with a very good levelling and quick drying. In white and bright shades, it may show a slight yellowing if exposed to sunlight.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,10 - 1,25
Grinding Fineness (μ)	10 - 20
Supply viscosity at 20°C	70 - 80 KU (Stormer)
%Solids content (weigh / volume)	53 - 61 % weight; 41 - 45 % volume.
V.O.C. (g/l)	591 (Ready to use)
Type of product	Modified Alkyd
Colour	URKI-SYSTEM

SURFACE PREPARATION

On steel, deoxidized and degreased.
If a better adhesion and anti-rust protection is required, use F-862, F-25 or F-29 Synthetic Primers.

APPLICATION INSTRUCTIONS



25 ± 5"
FORD nº 4



URKISOL 300
25-30 %



30-40 my



3-4 h.Tack free



AIR-MIX
URKISOL 300
10-15 %



AIR-LESS
URKISOL 300
10-15 %

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	12 - 13 (35 my)
Gloss 60°-60°	> 70 %
Second layer	Before 1 h. or after 3 days.

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended. Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.