

Pre-Catalysed Enamels



A range of easy-to-use pigmented coatings. The primers are fast drying with good levelling, and easy sanding. The enamels are fast drying, and give finishes with good feel and surface slip. Recommended where superior resistance to Nitrocellulose is required, and where ease of application and repair are more important than durability.

Always stir well and check shade and sheen before use.

Primers

Pre-Catalysed White Primer
Pre-Catalysed High Opacity White Primer
Pre-Catalysed Black Primer

Number

ND2012-9001
ND2001-9001
ND2501-7001

Sheen

N/A
N/A
N/A

Viscosity

10 - 17 poise
10 - 17 poise
100 - 110 secs

Enamels

Pre-Catalysed Enamel White Matt
Pre-Catalysed Enamel White Semi Matt
Pre-Catalysed Enamel White Eggshell
Pre-Catalysed Enamel White Gloss
Pre-Catalysed Enamel Black Matt
Pre-Catalysed Enamel Black Semi Matt

Number

NG2502-90011
NG2502-90012
NG2502-90013
NG2502-90019
NG2502-70011
NG2502-70012

Sheen

10%
20%
30%
Gloss
10%
20%

Viscosity

27 - 35 secs
27 - 35 secs
27 - 35 secs
27 - 35 secs
27 - 35 secs
27 - 35 secs

Available in Pastel Tints and most strong colours

SG / Coverage

Primers approx 1.2 / 8 square metres per litre
Enamels 1.0 / 7 square metres per litre

Application

Standard products are for conventional spray.

Primers and Enamels spray as supplied, or plus 5 - 10% thinners.

Consult BA Technical Department for use with other spraying techniques.

Special products are available for curtain and roller coating.

Air pressure: 35 - 45 psi

Fluid pressure: 10 - 15 psi

Note: Pre-Catalysed Lacquers and Enamels should not be applied over sealers and Primers containing stearates.

Drying

Touch Dry: 15 - 20 mins

These times may be reduced by force drying.

Sanding Recoating: 60 - 90 mins

Packing: Overnight minimum

Thinners

Dual Thinners: NT2511

Cleaning Fluid

NT2013

Retarder Solutions

Weak: NT2505

Strong: NT2514

Limitations

Not recommended for use on horizontal working surfaces in laboratory, kitchen or bar situations.

Packaging

Available in 5, 25 and 205 litre containers.

Health & Safety

Refer to Health and Safety Data Sheet for individual products

Becker Acroma

Rookwood Way, Haverhill, Suffolk CB9 8PQ

Tel: 01440 703611 Fax: 01440 761091

www.beckeracroma.co.uk



Becker Acroma