

PINTURAS JUNO

DATA SHEET

JUNOMALTE GLOSS -P-

CODE: 88911

DESCRIPTION

This gloss synthetic enamel is based on high -quality alkyd resins, and is suitable for both indoor and outdoor decoration jobs.

USAGE: INDOOR - OUTDOOR

Indoor-Outdoor paint for timber, metal, joinery and coverings.

CHARACTERISTICS

• Finish	Gloss
• Colour	Achieves colours from Ral and NCS, Coltec, etc.
• Density	1.15 +/-0.05 g/cc S/FR1001
• Drying time	To dust: 4 hour
	To the touch: 8 hours
	Second coat: Minimum: 24 hours
	Maximum: 8 days
• Diluent	D-16 or White Spirit
• Flash point	Flammable (21° - 55° C)
• Coverage	10 - 14 m ² / L
• VOC content	Max 400 g/l

SURFACE PREPARATION

TIMBER

It must be clean and dry, grease-free and sanded. Prime with **Hangers Synthetic Sealer**.

IRON AND STEEL

Once grease and rust are removed, prime with **Metalex Red Lead** or an appropriate antioxidant agent.

ALUMINIUM & GALVANISED SURFACES

Once cleaned, prime with **Multipurpose Primer**.

Previously painted surfaces, when in good condition, can be painted directly once washed and lightly sanded in order to fully remove the gloss. If the paint is in a poor condition, it must be thoroughly removed. Clean up and treat as new.



PINTURAS JUNO

B° Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32

INTERNET:www.juno.es - E-MAIL: infoweb@juno.es

APPLICATION INSTRUCTIONS

Use a suitable brush or enamel roller directly and spread the paint evenly. For spray painting dilute with 10-15 % of **D-17**, **never exceeding 30- 35 dry microns per coat in both cases.**

Temperature: The application temperature must be between +5°C and + 35°C.

CLEANING

D-16 Solvent or Universal Solvent.

REPAINTING

With alkyd resin based enamels thinned with **White Spirit or Turpentine.**

OBSERVATIONS

Stir the recipient contents thoroughly until evenly mixed.

When less opaque colours are used, such as reds, yellows or oranges, applying a similar colour undercoat with good coverage properties is recommended.

PACKAGING

Lithographed metal container. Sizes: 0.750 and 4 litres.

Date: December 2006/Revision: 4

N.B.: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, it must only be construed as an indication **WITHOUT LIABILITY** even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the procedures and purposes intended. The application, use and processing of the products supplied by us are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32

INTERNET:www.juno.es - E-MAIL: infoweb@juno.es