

PINTURAS JUNO

DATA SHEET

NATUR-SELL

CODE: 21100

DESCRIPTION

A primer sealer based on aqueous-dispersed acrylic resins and selected pigments, which provide high resistance and flexibility.

USAGE: INDOOR - OUTDOOR

Wood and masonry surfaces.

CHARACTERISTICS

- | | |
|---------------------------|--|
| • Finish | Matt |
| • Colour | White |
| • Viscosity | Min 25 P S/FR 1007 |
| • Density | 1.35 +/-0.05 S/FR1001 |
| • Drying time | To the touch: 1-2 hours |
| | Second coat: Minimum: 12 hours |
| | Maximum: Indefinite |
| • Diluent | Water |
| • Solids in volume | 42% theoretical |
| • Health & Safety | Aqueous-phase paint product: exempt from labelling |
| • Guidance coverage | 8 - 10 m ² / Lt / coat |
| • VOC content | Max 50 g/l |

SURFACE PREPARATION

WOOD

It must be clean and dry, grease-free and sanded. Before applying the finishing coat, sanding down the surface is recommended.

MASONRY

Surfaces must be dry and efflorescence-free, and in the case of cement and plaster, also neutralised with 10% Hydrochloric Acid or vinegar. Rinse with water and allow to dry.

Previously painted surfaces, when in good condition, can be painted directly once washed and lightly sanded in order to fully remove the gloss. If the paint is in a poor condition, it must be thoroughly removed. Clean up and treat as new.



PINTURAS JUNO

Bº Sacconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32
INTERNET:www.juno.es - E-MAIL: infoweb@juno.es

APPLICATION INSTRUCTIONS

Brush, roller or spray gun.

DYING

Use **Junoral Colorant** with water, at ratios not exceeding 3 %.

CLEANING

Water

REPAINTING

Any synthetic, epoxy or polyurethane based enamel can be used for repainting.

OBSERVATIONS

Stir the recipient contents thoroughly until evenly mixed.

PACKAGING

Metal container. Sizes: **0.750 and 4** litres.

Date: January 2007/Revision: 3

N.B.: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, it must only be construed as an indication **WITHOUT LIABILITY** even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the procedures and purposes intended. The application, use and processing of the products supplied by us are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32
INTERNET:www.juno.es - E-MAIL: infoweb@juno.es