



ISOPON ZINC 182

Anti-Rust Primer Coating

Description	ISOPON ZINC 182 is a highly effective rust inhibiting primer. It can be applied to all ferrous metal surfaces provided the loose rust is removed. Complete removal of all rust will improve its effectiveness. The hardened ISOPON ZINC 182 forms a tough durable surface onto which paint can be applied. Once applied ISOPON ZINC 182 will provide first class rust protection to ferrous surfaces.
Surface preparation and instructions for use	ISOPON ZINC 182 anti rust coat can be used on the following surfaces:- <ul style="list-style-type: none">• Bare metal use 180 grade paper. Re-clean and dry.• Existing paint surfaces degrease with a suitable spirit wipe or thinner. Wet flat with 400 grade paper.
Health and Safety Statement	<u>FOR PROFESSIONAL USE ONLY.</u> Read full instructions before use. IMPORTANT: This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at WWW.U-POL.COM . U-POL disclaim any liability where the user does not wear the recommended personal protective equipment.
Application	Stir paint in tin thoroughly before use. ISOPON ZINC 182 can be applied by brush, dip or spray gun. For aerosols shake thoroughly before use.
Thinners	ISOPON ZINC 182 is supplied ready for use for brush or dip applications. However up to 10% of good quality synthetic or cellulose thinners can be added to adjust viscosity for spray application. Use cellulose thinners or similar proprietary products to clean brush or gun after use.
Build & Pressure	For spray application a pressure of between 2.76 - 4.82 BAR is required at the gun. One coat of ISOPON ZINC 182 will give a build of approximately 40-60 microns.
Drying Time	Approximately 3-4 hours drying is required between coats, two coats are normally sufficient to give a satisfactory coating. ISOPON ZINC 182 will be ready for overcoating if left overnight to dry. The paint film can be baked at temperatures up to 120°C. Drying time is dependent on film thickness, humidity and temperature.
Over-painting	ISOPON ZINC 182 may be over-painted with most paint systems. Abrade lightly with 240 grit paper before over-painting.
Product Codes	Z182/A - 150ml aerosol Z182/2.5 - 2.5L tin. Z182/S - 250ml tin Z182/AL - 450ml aerosol Z182/M - 1L tin.

U-POL, 1 TOTTERIDGE LANE, WHETSTONE, LONDON, N20 0EY, UK

Home Sales T: +44(0)870 899 8200; F:+44(0)870 899 8211; E: sales@u-pol.com

Export Sales T: +44(0)870 899 8200; F:+44(0)870 899 8299; E: exportsales@u-pol.com

Technical T: +44(0)870 899 8310; F:+44(0)870 899 8351; E: technicaldepartment@u-pol.com

ISOPON™

WEBSITE: WWW.U-POL.COM