



Product Description	Twin component, solvent based two component transparent polyurethane undercoat
Properties	Quick hardening Quick and easy manual or machine sanding
Recommended use	Product suitable for sealing wooden joins and indoor furniture
Certificados	Certificado.de.Producto.Simbolo.de.Calidad.AIDIMA



Technical Characteristics

	Norma	Value
Solids by weight (%)	UNE EN ISO 3251	37% ± 2
Viscosity (Ford cup 4)	UNE EN ISO 2431	200" ± 10
Density (Kg/L)	UNE EN ISO 2811-1	0.960+/-0.020

Mixing Characteristics

Hardener		CATALIZADOR N. 312
Mix Proportion (% Volume)		50%
Mix Solids (%)	UNE EN ISO 3251	32% ± 2
Viscosity of mix (Ford cup 4)	UNE EN ISO 2431	22" ± 5
Pot life mixture	UNE EN ISO 9514	4 to 5 hours at 20°C

Application Characteristics

Application System	Aerographic and airless
Recommended thickness of coat	150-180 gr/m ²
Touch-dry	25 a 40 minutes (depending on thickness and temperature)
Surface sanding	4 - 5 hours, depending on thickness applied and ambient conditions
Sanding	16 - 24 hours, depending on thickness applied and ambient conditions

Remarks re application process

- If you wish to seal the wood pores, you must sand the first undercoat before applying a second coat
- In the case of an increase in viscosity after the application, reduce with .9130
- If the ambient temperature is high, use .9020 to dilute
- On this undercoat you can apply any LACAPOL or NITROBARP top coat

Remarks

- Shake contents of containers before use.
- Apply with good air renewal.
- Do not store opened or started containers.
- Maximum stability of hardener is less than 6 months at 20°C.
- For toxicological standards, consult FICHA DE SEGURIDAD.
- Keep out of the reach of children.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any

undesired consequence deriving from its use. 29-02-2012 This sheet replaces all previous versions.
