

		sour based on epoxy resins reliculated with polyamide				
Recommended use	Suitable fo floors.	r garages, workshops, wine ce	llars, industrial units, factories, car parks and concre			
Properties	Easy to apply					
	Filling power Resistant to abrasion, to wear, mopping, oil spills, mineral oil, other chemical agents and dirt general Eliminates the formation of dust on the floor, improves surface hardness, avoids erosion and wea and tea making the floor easier to clean and more decorative.					
				Good properties in terms of hardness, elasticity and aesthetic appearance.		
				Characteristics of supply		
			Normativa	Specified		
Colour		UNE EN ISO 3668	See colour chart			
Gloss(geometry 60°)		UNE EN ISO 2813	Semi-gloss			
Specific weight (Kg/L)		UNE EN ISO 2811-1	1.57 ± 0.05 (depending on colours)			
Solids by weight in the mixture (%)		UNE EN ISO 3251	67% ± 3 (depending on colours)			
Solids by volume in the mixture (%)		UNE 48090-82 (ISO 3233)	53% ± 3 (depending on colours)			
Theoretical yield of the mixture (m ² /l)		UNE 48 282-94	7 - 9 m²/l, coat, depending on conditions of surface			
Conservation and Stability of the Container		UNE 48 083-92	9 months unopened, in original packaging. Store ir a cool., dry place, away from frosts. Temperature range: 5-40°C			
Application Instructions						
Application equipment			Roller and round brush			
Hardener			K0710			
Mix proportion by			3/1			
volume Mix shelf life			>8 hours			
Application solvent		UNE EN ISO 9514	Reference: .9734			
Drying / Polymerisation						
Air drying (20°C-60% R.H.)		UNE 48301	(Touch) 5-6 hours			
Repainting			12 - 24 hours			
Remarks						
See general conditions						

See general conditions

Apply the product when use and curing is at temperatures over 10°C. At the same time the paint temperature must also be over the limit value

It is important to ventilate well during application on closed surfaces and subsequent polymerisation

Do not store opened or started containers.

For toxicological standards, consult FICHA DE SEGURIDAD.

Apply with good air renewal.

Shake contents of containers before use.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 31-10-2019 This sheet replaces all previous versions.



PINTURA EPOXI SUELOS AL DISOLVENTE TINTOMETRIA

Oficinas centrales / Headquarters / Siège social San Fernando, 116. D.P. 26300 Nájera. La Rioja. Spain Tel. (34) 941 410 000 / Fax (34) 941 410 111 / www.barpimo.com