

## SPORTS TRACK PAINT

**Product Description**

High-quality decorative paint for sports courts based on acrylic resins in aqueous dispersion and high solidity pigments.

**Colour chart**

Pavement paint chart



### Technical features

<b>Colour</b> UNE EN ISO 3668	White, Chrome Green and Tennis Red.
<b>Shine (geometry 60°)</b> UNE EN ISO 2813	Semi-matt
<b>Specific weight (Kg/L)</b> UNE EN ISO 2811-1	1,350-1,550 Kg/L depending on colour.
<b>Solids by weight (%)</b> UNE EN ISO 3251	60-67% depending on colour
<b>Solids by volume (%)</b> UNE EN ISO 3233-1	47 ± 2 %
<b>Viscosity rating</b> UNE 48076	100 ± 4 KU at 20°C.
<b>Theoretical Performance</b>	7-9 m <sup>2</sup> /l coat, depending on surface structure and conditions.
<b>Preservation and stability in container</b>	Excellent up to one year in original, unopened container, under normal temperature and humidity.
<b>VOCs (g/l)</b> UNE EN ISO 11890-1	515-595 g/L depending on colour.
<b>Thinner</b>	Water.

## Application instructions

<b>Application</b>	Suitable for protecting and decorating concrete, cement mortars, asphalt, sports facilities, tennis courts, and gables surfaces.
<b>Application temperature</b>	Above 8°C.
<b>Surface temperature</b>	Above 8°C.
<b>Relative environmental humidity</b>	Below 80%
<b>Surface moisture</b>	Below 8%
<b>Number of coats</b>	2-3
<b>Recommended layer thickness</b>	30 - 40 microns per coat
<b>Subsequent</b>	After 3-5 hours

	<b>Thinner</b>	<b>Application percentage</b>
<b>Brush</b>	Water.	1st coat slightly diluted (10% maximum), 2nd and 3rd coats as is or slightly diluted (5% maximum).
<b>Roller</b>	Water.	1st coat slightly diluted (10% maximum), 2nd and 3rd coats as is or slightly diluted (5% maximum).
<b>Airless gun</b>	Water.	Depending on the nozzle and pressure used in the application.

<b>Thinner for cleaning</b>	Water.
<b>Cleaning of utensils</b>	Clean with water immediately after.

## Properties and Instructions for use

### Properties:

Easy to apply.  
Great hiding power.  
Adhesive, decorative, hard and flexible finishes.  
Resistant to abrasion, erosion, wear and weathering.  
Eliminates dust formation in the ground and improves surface hardness.

### Surfaces preparation:

Surfaces must be sanded, clean, dry, free of grease, salt, old paints, consistent, free of loose parts, crumbly and peeling.

Preferably on rough surface for a better adhesion.

On unpainted surfaces: Apply 2 or 3 coats of the same product. First coat slightly diluted (10% maximum) with water, the 2nd and 3rd coats slightly diluted (5% maximum) or as is.

On surfaces with old paint: Remove deteriorating, soft, crumbly, peeling, etc. paint. Seal properly with SELLAFOND (Ref. 1764) and proceed as on unpainted surfaces.

### Instructions for use:

Stir the contents of the container well.  
Apply with good air renewal, in thin, uniform and well spread coats.

## Drying / Polymerisation

<b>Air drying (20°C and 80% R.H.)</b>	30 minutes depending on thickness applied and environmental conditions.
<b>Minimum repainting interval</b>	3-5 hours
<b>Drying for Physical Tests</b>	15 days

## Physical-chemical resistances

<b>Test Tube</b>	Concrete and/or fibre cement.
<b>Dry Film Thickness</b> UNE-EN ISO 2808	100 ± 10 microns
<b>Adherence</b> UNE-EN ISO 2409	100% concrete.

## General

<b>Packaging</b>	4l and 15 l.
<b>Storage</b>	Store in a cool place. Do not store open containers.

## Comments

Shake the contents of the containers before use.  
For toxicological regulations, please check the SAFETY DATA SHEET.  
Apply in a well ventilated area.  
Store in premises protected from frost.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For these reasons, we cannot accept any undesired consequence deriving from its use. 20-04-2016 This sheet replaces all previous versions.