

FONDIPOL IGNIFUGO BLANCO



Product Description	White twin component solvent based pigmented polyurethane undercoat Alkyd nature
Properties	Excellent covering High opaqueness
Recommended use	Primer to use on furniture requiring FLAMEPROOF PROPERTIES
Certificates	UNE EN 13501-1:02 C-S2 d0
Certificados	Certificado.de.Producto.Simbolo.de.Calidad.AIDIMA , Fondipol.y.lacapol.ignifugos.pdf



Technical Characteristics

	Norma	Value
Solids by weight (%)	UNE EN ISO 3251	68%+-2
Viscosity (Ford cup 6)	UNE EN ISO 2431	57" ± 3
Density (Kg/L)	UNE EN ISO 2811-1	1.340+/-0.015

Mixing Characteristics

Hardener		CATALIZADOR N.275
Mix Proportion (% Volume)		50%
Mix Proportion (% Weight)		40%
Mix Solids (%)	UNE EN ISO 3251	57% ± 2
Viscosity of mix (Ford cup 4)	UNE EN ISO 2431	50" ± 5
Pot life mixture	UNE EN ISO 9514	6 to 7 hours at 20°C
Solvent		Reference: .9130
Percentage dilution		10-15%

Application Characteristics

Application System	Aerographic, airless and curtain
Application on	DM fire resistant
Recommended thickness of coat	150-180 gr/m ²
Touch-dry	50 a 80 minutes (depending on thickness and temperature)
Surface sanding	6 - 7 hours, depending on thickness applied and ambient conditions
Sanding	16 - 24 hours, depending on thickness applied and ambient conditions

Remarks re application process

- In the case of an increase in viscosity after the application, reduce with .9130
- If the ambient temperature is high, use .9020 to dilute
- For application onto MDF, first it is necessary to apply an insulating sealant undercoat.

TO HAVE A FIREPROOF SYSTEM IT IS COMPULSORY TO APPLY WHITE FIREPROOF LACAPOL OVER SANDED, DUST-FREE WHITE FIREPROOF FONDIPOL, IN A QUANTITY OF 120 g/m²

Remarks

- Shake contents of containers before use.
- Apply with good air renewal.
- Do not store opened or started containers.
- Maximum stability of hardener is less than 6 months at 20°C.
- For toxicological standards, consult FICHA DE SEGURIDAD.
- Keep out of the reach of children.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 21-12-2010 This sheet replaces all previous versions.