

URKI-LON

FLEXIBLE ENAMEL FOR CANVAS AWNINGS

URKI-SYSTEM

CONVERTER: 6480 / CONV U-LON

RELATION PASTE / CONV.: 17/83 Volume (25/75 weight)

Edition: 020 2011/11

Cod: 694800000.00000.020

APPLICATION

Specifically developed for the painting and labelling of PVC tilts.
Outstands for its quick drying, flexibility and adhesion.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	0,96 - 1,12
Grinding Fineness (μ)	10 - 15
Supply viscosity at 20°C	115 - 135 sec. Ford Cup nº 4
%Solids content (weight / volume)	40 - 50 % weight; 32 -35 % volume.
V.O.C. (g/l)	696 (Ready to use) - (2004/42/CE) IIB (E) (840)
Type of product	Acrylic
Colour	URKI-SYSTEM

SURFACE PREPARATION

Check whether it is P.V.C. tilts.
The surfaces to be painted should be degreased with Thinner n. 94.

APPLICATION INSTRUCTIONS

Important: Please, take the recommended thickness into account in order to avoid problems during the drying process, as well as cracking due to an excessively thick coat.



15-18"
FORD nº 4



URKISOL 500
60-70 %



20-25 my



30' Tack Free

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	13 - 14 (25 my)
Gloss 60°-60°	55 - 65 %
Second layer	1 h.

Mixing (weight) with F-755 Universal MAtcher, lower gloss levels can be obtained.

URKI-LON	95	90	75
F-755	5	10	25
Gloss 60°-60°	25-35	15-20	3-5

The values shown in the table are for guidance only.

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.
Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.