

TECHNICAL DATA SHEET

BERNARDO ECENARRO, S.A.

Poligono Industrial San Lorenzo s/n 20870 Elgoibar (SPAIN) Tel.: +34 943 74 28 00

Fax: +34 943 74 28 00 Fax: +34 943 74 06 03 www.bernardoecenarro.com

Page 1 from 1

Edition: 020 2011/11

Cod: 7075200000097.00000.020

2 K URKI-SPRAY

2K ACRYLIC CLEARCOAT

APPLICATION

2K Acrylic Clearcoat for spot repair in two coat systems. Outstands for its high antiscratch, oil and outdoor resistance, as well as the quick drying and leveling. The finish is the same as the conventional 2K spray gun product.

PHYSICAL PROPERTIES

Type of produtc	Acrylic	
Colour	Transparent	
V.O.C. (g/l)	< 840 (Ready to use on Spray) - (2004/42/CE) IIB (E) (840)	

SURFACE PREPARATION

Apply directly on Matt Base Coat (both solvent and water based), at least 30 Minutes after the application of the Base Coat.

APPICATION INSTRUCTIONS

Check the indicated steps on the base of the can for the mix Binder/ Hardener. Leave in two layers, with 5- 10 minutes between layers.

After use, turn upside down and press the nozzle to clean it (Potlife 24 hours)



Spraying Distance 20-30 cm



40-50 my



Tack Free 30 Dry3 h.



12-15 min.



10-15 min. 60°C/30 min.



60°C/45 min. Air Drying 7-8 h.



24 h

FEATURES OF DRY FILM

Gloss 60°-60°	100 %	
Second layer	24 h	

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended. CAUTION: In any case the can must be above 50°C.

Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.