

TECHNICAL DATA SHEET

BERNARDO ECENARRO, S.A.

Poligono Industrial San Lorenzo s/n 20870 Elgoibar (SPAIN)

Tel.: +34 943 74 28 00 Fax: +34 943 74 06 03 www.bernardoecenarro.com

Page 1 from 1

Edition: 021 2013/01

Cod: 3700307470.00000.021

PROTEC-BRUSH

1 K BRUSHABLE SEALANT

APPLICATION

1 K Brushable and recoatable elastic sealant. Suitable for old and new welded edges, joints and similar in the construction, car and metal industry, buses, containers and air ventilation industry.

PROTEC-BRUSH remains permanently flexible absorbing vibrations in the sealed moving parts.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,19 - 1,25
Grinding Fineness (µ)	
Supply viscosity at 20°C	Thixotropic
%Solids content (weigth / volume)	62 % ± 2 %
V.O.C. (g/l)	399 (Ready to use) - (2004/42/CE) IIB (E) (840)
Type of produtc	Rubber
Colour	Grey 7470

SURFACE PREPARATION

The surface must be dry, free from grease and rust. In order to achieve a better adhesion of the product, remove flaking paint, dirt or rust.

APPLICATION INSTRUCTIONS

-Apply 1 or 2 coats.



FEATURES OF DRY FILM

Theoretical yield (m²/l)	1,8 (300 my)
Gloss 60°-60°	Satin
Second layer	30 'possible, recommended after 12 hours

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 25°C recommended. Can life: 2 years from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.