

TECHNICAL DATA SHEET

BERNARDO ECENARRO, S.A.

Poligono Industrial San Lorenzo s/n 20870 Elgoibar (SPAIN) Tel.: +34 943 74 28 00

Fax: +34 943 74 26 00 www.bernardoecenarro.com

Page 1 from 1

Edition: 020 2011/11

Cod: 6027809006.00000.020

F-4101 A

HEAT RESISTANT ALUMINIUM UP TO 450°C

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Heat Resistant Paint up to 450°C, modified special Resin-based with Silicon and high-quality Aluminium Pigment. It provides metalized top coats with perfect reistance to continuos temperature exposure, such as for exhausts, ovens, electric material, etc.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,20 ± 0,05
Grinding Fineness (µ)	Without lumps
Supply viscosity at 20°C	60 - 70 KU
%Solids content (weigth / volume)	52 % ± 2 weight; 34 % ± 2 volume.
V.O.C. (g/l)	560
Type of produtc	Siliconing Alkyd
Colour	Greyish Aluminium

SURFACE PREPARATION

The surfaces should be free from rust and dirt, and thoroughly degreased. Sand-blasting is recommended at grade Sa 2,5.

APPICATION INSTRUCTIONS



15-20" FORD nº 4



Supply



URKISOL 170 30-35%



20-25 m



Touch free 15' Tack free 30' 100°C/15min



5-10

FEATURES OF DRY FILM

Theoretical yield (m²/l)	13 - 14 (25 my)
Gloss 60°-60°	Matt < 5 %
Second layer	Wet on wet (30 min. intervale)

Note: This product achieves its characteristics once it is cured by temperature.

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended. Can life: **1 year** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.