

# PRO2KClear

## Product Description

Pro2kClear is a superior high gloss crystal clear finish that has excellent gloss retention. This product is easy to activate and apply with mechanical polishing possible after 24 hours.

## Product Features

- Genuine two pack technology
- In-can activator system
- Spray gun finish
- Contains isocyanate
- 200ml to reduce wastage
- Extremely scratch resistant and highly resistance to fuel, UV-radiation and weather influences
- Quick drying-time



## Usage

- Spot repairs
- Refinishing of individual parts.

## Pre Treatment

ProXL 2k clear can be applied to air drying basecoats after 30 minutes air drying time.

We've got it covered from...

.....start to finish

## Application


### Mixing of ProXL 2K Clear with activator:



Remove cap from the bottom of the can. Remove the ring and feed the ring through the hole in the bolt.



Pull the bolt in the bottom of the can with the aid of the metal ring as far as it will go.



By twisting 360°, the activator will be completely released



Shake the can for 2 mins to ensure that the activator is completely mixed with the lacquer.



After use, clear the valve by turning the aerosol upside down, pressing the nozzle for approx. 5 seconds.

Pot life: approx. 24 hours.


## Product Properties




2-3 full spray passes, 50µ




Infra-red drying time 25 min.



Flash-off time between coats: approx. 2 minutes



Polishing after 7h 70°F (20°C), air-drying 45 min. 140-160°F (60°C), oven drying or infra-red drying 30 min.



Air-drying 70°F (20°C) 7h or 25 min.  
 140-160°F (60°C) object temperature

**We've got it covered from...**

**.....start to finish**

