

POLPARQUET TOP



Product Description Properties

Transparent, special two-component polyurethane for wooden floors
Easy to apply
High level of hardness and physical resistance.
High resistance to abrasion
Good share uniformity

Recommended use Certificados

Product recommended for processes for application on to parquet flooring
[Certificado.de.Producto.Simbolo.de.Calidad.AIDIMA](#)



Technical Characteristics

| | Norma | Value |
|------------------------|-------------------|-----------------------|
| Solids by weight (%) | UNE EN ISO 3251 | 38+-2% |
| Viscosity (Ford cup 4) | UNE EN ISO 2431 | 30"+-5 |
| Density (Kg/L) | UNE EN ISO 2811-1 | 0.995+/-0.020 |
| Shine (60° angle) | UNE EN ISO 2813 | Matt, satin and gloss |

Mixing Characteristics

| | | |
|-------------------------------|-----------------|-------------------|
| Hardener | | CATALIZADOR N.381 |
| Mix Proportion (% Volume) | | 100% |
| Mix Solids (%) | UNE EN ISO 3251 | 33% ± 2 |
| Viscosity of mix (Ford cup 4) | UNE EN ISO 2431 | 15" ± 3 |
| Pot life mixture | UNE EN ISO 9514 | 24 hours |

Application Characteristics

| | |
|--------------------|--|
| Application System | Aerographic and roller |
| Touch-dry | 1 - 3 hours, depending on thickness applied and ambient conditions |
| Total hardening | 2 days |

Remarks re application process

Process: FONDIPOL 1001 / K91 (50%).

Sanding.

Polparquet Top / K381 (100%)

If you want to apply a second coat of Polparquet sand the first one beforehand.

In the case of resinous wood, before the undercoat apply a coat of ISOLANT PRIMER HQ / K105 (100%)

In the case of an increase in viscosity after the application, reduce with .9130

If the ambient temperature is high, use .9020 to dilute

In the gloss version the product has lower viscosity.

Physical Chemical Resistance

| | Norma | Value |
|-----------------|-----------------|---------------|
| Persoz hardness | UNE-EN ISO 1522 | 300" 24 hours |

Remarks

- Shake contents of containers before use.
- Apply with good air renewal.
- Do not store opened or started containers.
- For toxicological standards, consult FICHA DE SEGURIDAD.
- Keep out of the reach of children.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 01-09-2020 This sheet replaces all previous versions.