

Pro2KPRIME

2K Primer Filler

PRO2KPRIME is a 2K primer-filler that can be applied to a wide range of substrates with outstanding adhesion and sealing properties. It is very quick drying and isocyanate free.

- Genuine 2K high build primer filler
- Excellent adhesion to a wide range of substrates
- Very quick drying


Suitable substrates

Suitably prepared steel, aluminium and galvanised steel. Cleaned and sanded PE fillers as well as plastics pretreated with ProXL

Application data



2-3 coats @ 50µm



| | |
|---------------|-------------------|
| Between coats | 3 minutes @ 20°C |
| Sanding | 45 minutes @ 20°C |
| Wet on wet | 20 minutes @ 20°C |



15-20 Minutes



P800-1000



P400-500

Application method



1 Remove cap off the bottom of the can. Remove the ring and feed through the hole in the bolt.



2 Pull the bolt in the bottom of the can with the aid of the metal ring as far as it will go.



3 By twisting 360°, the activator will be completely released



Pro2KPRIME

2K High Build Primer

Application method - continued



Before use, shake the aerosol for 2 minutes and spray a sample area.



Apply in cross coats from a distance of 250mm from object.



After use turn aerosol upside down, press the nozzle for approx. 5 sec and clear valve.

Technical data

| | |
|------------------------|--|
| Chemical base | Acrylic Resin |
| Temperature resistance | Up to 80°C |
| Pot life | 24 hours @ 20-25°C 5 days @ 6°C |
| VOC content | 139 g/200ml |
| Coverage | 0.75m ² |
| Storage notes | 3 years in appropriate storage (-10°-25°C, relative air humidity of max. 60%) |

Environmentally sound:

The products supplied by ProXL are 100% free of heavy metals and the caps and packaging are made of recyclable material.

Disposal:

Completely emptied cans should be put in recycling skips or appropriate container. Cans which are not empty should be disposed off as special refuse.

This application and technical information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively is the responsibility of the user.

