



DOLPHIN GLAZE

SELF LEVELLING FINISHING GLAZE

| | |
|---|--|
| Description | <p>DOLPHIN GLAZE polyester finishing glaze is a two component multifunctional chemical liquid used for final skimming of a polyester glaze repair or for direct application onto minor imperfections on bodywork prior to over painting.</p> <p>DOLPHIN GLAZE has been specially formulated for the professional user and combines excellent leveling properties together with easy sanding.</p> |
| Surface Preparation & Instructions For Use | <p>DOLPHIN GLAZE polyester finishing glaze can be used on the following surfaces:-</p> <ul style="list-style-type: none">• Bare metal – e.g. Steel, degrease and abrade with P80 paper.• Aluminium, Galvanised and Zinc coated substrates – degrease and abrade with P120 paper. Do not apply over etch primer.• Original paint surfaces (with the exception of thermoplastic acrylics) – degrease and abrade with P180 grit paper.• GRP – degrease and abrade with P80 grit paper. |
| Health and Safety Statement | <p>FOR PROFESSIONAL USE ONLY. Read full instructions before use.</p> <p>IMPORTANT: This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at WWW.U-POL.COM. U-POL disclaim any liability where the user does not wear the recommended personal protective equipment.</p> |
| Mixing Ratio | <p>100 parts by weight DOLPHIN GLAZE polyester glaze, 2 parts by weight U-POL hardener for polyester.</p> <p>A simple guide would be to mix a 3" diameter circle (roughly size of a tennis ball) of Dolphin Glaze to one "pea" size of hardener. The exact mixing ratio is not critical, although over or under catalyzation may affect the gel time.</p> <p>DOLPHIN GLAZE is a thick liquid and should be mixed in small quantities on a flat non-porous surface. To obtain optimum results apply the mixed liquid in small quantities to form a thin film – during cure, surface imperfections will flow out to leave a level repair which requires only a small amount of sanding. Do not greatly over catalyze the paste as this will not significantly speed up the gel time and could lead to bleed through and bleaching problems when over-painting later. Staining may also occur where too little hardener is used.</p> |
| Pot Life | Once mixed, 4-5 mins. at 20°C with 2% hardener. |
| Tools | Mixing board, filler knife, plastic or rubber spatula. |
| Drying Time | Sandable after 20 mins. at 20°C. |
| Over-Painting | DOLPHIN GLAZE polyester finishing glaze can be over-painted with most paint systems including 2K. Ideally a full system is recommended including primer. |
| VOC Information | The EU limit for this product (product category: IIBb) in ready to use form is 250g/litre. The VOC content of this product in ready to use form is 100g/litre |

U-POL, 1 TOTTERIDGE LANE, WHETSTONE, LONDON, N20 0EY, UK
Home Sales T: +44(0)870 899 8200; F:+44(0)870 899 8211; E: sales@u-pol.com;
Export Sales T: +44(0)870 899 8200; F:+44(0)870 899 8299; E: exportsales@u-pol.com;
Technical T: +44(0)870 899 8310; F:+44(0)870 899 8351; E: technicaldepartment@u-pol.com;
WEBSITE: WWW.U-POL.COM