

**Dynamol**

**CODE: 9.500**

**DESCRIPTION**

Chloro-rubber resin and unsaponifiable plasticizer based paints specially designed to protect metallic surfaces and masonry.

**INTERIOR AND EXTERIOR USE**

Due to its high resistance to acids and alkalis it is recommended for surfaces in industrial environments.

Paint for road signs, garages, sports facilities etc. ..

Not recommended for painted surfaces coated with tar and / or bituminous asphalt.

**FEAUTURES**

W	Finish	.....	Satin
W	Colors	.....	White, black, grey, red, red 16, green and yellow.
W	Viscosity		90 minimum S/FR1002 poises
W	Density	.....	1,40; 1,50 s/FR 1001
W	Drying	.....	1 hour to the touch
	Volume of solids		Repaint: Minimum 24 hours. Maximum: undefined 33% theoretically
W	Thinner	.....	D-40
W	Performance	.....	8 m2/l. (estimation)
W	COV's content	.....	Maximum 500 g/l.

**SURFACES PREPARATION**

Iron & Steel:

Primer with Chloro-rubber primer after grease, rust and calamine have been removed.

Aluminum and galvanized

Primer after cleaning with Dynapok Zinc Phosphate 2/C multisupport primer.

Masonry

New or old unpainted and silica-free concrete surfaces should be washed with a 10% hydrochloric acid-water solution, and then rinsed thoroughly and left to dry for 2 days.

Appropriate safety precautions should be followed.



PINTURAS JUNO

## APPLICATION PROCESS

Apply using a roller, brush or gun

Gun spray requires a dilution with 10-15% D-40.

It is necessary to remove old paint from old painted surfaces.

On concrete floors, whitewash and curing agents must be removed by applying soda blasting or milling operation, vacuum later. As a result, a rough surface free of foreign materials will be obtained, which will result in better results and adherence.

Once the surface is ready, a first coat should be applied using a paint roller to promote penetration. Following coats should be applied every 24 hours.

## DYING

Using Universal colorant, no more than 3% colorant.

## CLEANING

D40 thinner or Universal solvent.

## REPAINTING

Same product

## COMMENTS

Stir well until completely a homogeneous mixture is achieved.

Before applying Dynamol, assure the any previously applied paint is compatible with chlororubber.

Applying the product to wet or excessively hot surfaces is not recommended.

Sport installations and courts cannot be used for 7 days after painting.

## PRESENTATION

Lithographed can: Size 4 and 15 liters

N.B: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, it must only be construed as an indication **WITHOUT LIABILITY** even in regard to possible third -party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the procedures and purposes intended. The application, use and processing of the products supplied by us are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.



**PINTURAS JUNO**