

PINTURAS JUNO

DATA SHEET

HANGERS SEALER

CODE: 21000

DESCRIPTION

A primer sealer based on alkyd resins and selected pigments, which provide high resistance and flexibility. It can be used as a primer or as a finishing coat for indoor applications.

USAGE: INDOOR - OUTDOOR

Wood and masonry surfaces.

CHARACTERISTICS

• Finish	Matt
• Colour	White
• Density	1.45 +/-0.05 S/FR1001
• Drying time	To the touch: 6 - 8 hours Second coat: Minimum 24 hours Maximum 8 days
• Diluent	D-16 or White Spirit
• Solids in volume	42 % theoretical
• Flash point	Flammable (21° - 55° C)
• Guidance coverage	8 - 10 m ² / Lt / coat
• VOC content	Max 450 g/l

SURFACE PREPARATION

WOOD

It must be clean and dry, grease-free and sanded.

IRON AND STEEL

Remove grease and rust, and prime with **Metalex Red Lead** or an appropriate antioxidant agent.

ALUMINIUM & GALVANISED SURFACES

Once cleaned, prime with **Multipurpose Primer**.

MASONRY

Surfaces must be dry and efflorescence-free, and in the case of cement and plaster, also neutralised with 10% Hydrochloric Acid. Next, apply **Hangers Sealer**.



PINTURAS JUNO

Bº Saconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32
INTERNET:www.juno.es - E-MAIL: infoweb@juno.es

Previously painted surfaces, when in good condition, can be painted directly once washed and light ly sanded in order to fully remove the gloss. If the paint is in a poor condition, it must be thoroughly removed. Clean up and treat as new.

APPLICATION INSTRUCTIONS

Brush, roller or spray gun.

For spray painting, dilute with 10 - 15 % **D-17**.

DYING

Use **Juno Universal Colorant** at ratios not exceeding 3 %.

CLEANING

D-16 Solvent or White Spirit

REPAINTING

With alkyd resin based enamels thinned with **White Spirit or Turpentine**.

OBSERVATIONS

Stir the recipient contents thoroughly until evenly mixed.

PACKAGING

Metal container. Sizes: 0.750/4 and 15 litres

Date: January 2007/Revision: 3

N.B.: Our technical instructions and advice, whether oral, in writing or through tests are given in good faith and to the best of our knowledge. However, it must only be construed as an indication **WITHOUT LIABILITY** even in regard to possible third-party industrial property rights, and this does not exempt the customer from testing the supplied products in order to verify their suitability for the procedures and purposes intended. The application, use and processing of the products supplied by us are carried out outside and beyond our control, and therefore, constitute the exclusive responsibility of the customer. If, however, there were any grounds to consider any liability on our part, this will be limited, regardless of the damage and loss, to the strict value of the goods supplied by us and used by the customer. It is understood that we guarantee the absolute quality of our products according to our General Sale and Supply Conditions.



PINTURAS JUNO

Bº Sacconi, 10-48.950 Erandio (Vizcaya)-Tel. 94-467 00 62-Fax 94-467 58 32
INTERNET:www.juno.es - E-MAIL: infoweb@juno.es