

HYDROBARP PELABLE BLANCO



Type of Product	Peelable water varnish
Recommended use	Acabado monocomponente pigmentado en base agua Temporary protection of varnished surfaces or other items such as joints, painting cabins, etc.
Properties	If the coat applied is sufficiently thick, it can easily be removed once dry.



Characteristics of supply

	Normativa	Specified
Gloss(geometry 60°)		Semi matt
Specific weight (Kg/L)	UNE EN ISO 2811-1	1.20 ± 0.02
Solids by Volume (%)	UNE 48090-82 (ISO 3233)	42% ± 2
Theoretical yield (m ² /l)	UNE 48 282-94	8-9 m ² /l (coat of 50 micras)
Supply viscosity	UNE-EN ISO 2431	90±5 K.U. at 20°C
COVS RD 117/2003 (Suministro) (Instalaciones)	UNE EN ISO 11890	1.176%

Application Instructions

Application equipment	Aerographic, airless and airmix
Spray nozzle	The nozzle diameter and the spray fan angle will be selected on the basis of the piece to be coated
Application solvent	Water
Recommended coat thickness	80-100 gr/m ²

Drying / Polymerisation

Touch dry	60 a 90 minutes (depending on thickness and temperature)
Hard dry	2 - 3 hours, depending on thickness applied and ambient conditions
Total dry	4 - 6 hours, depending on thickness applied and ambient conditions

Remarks

See general conditions

In air-dried water-soluble line products the atmospheric conditions of temperature and relative humidity are important, ideally 20°C and 65% R.H. for this reason it is recommended that you work with low-temperature ovens or stoves thereby ensuring that the drying is even throughout the year thanks to keeping them in the same conditions

Apply the product when use and curing is at temperatures over 10°C. At the same time the paint temperature must also be over the limit value

Shake contents of containers before use.

It is important to ventilate well during application on closed surfaces and subsequent polymerisation

Do not store opened or started containers.

Do not store at below 5°C
For toxicological standards, consult FICHA DE SEGURIDAD.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 11-03-2021 This sheet replaces all previous versions.