Reference: A4231

PAINT & PEEL LIQUID MASKING FILM WHITE




Type of Product	Peelable water based liquid masking film white.
Recommended use	Temporary protection of timber or metal surface surfaces.

Characteristics of supply

	Normativa	Specified
Gloss(geometry 60º)		Semi matt
Specific weight (Kg/L)	UNE EN ISO 2811-1	1.20 ± 0.02
Solids by Volume (%)	UNE 48090-82 (ISO 3233)	42% ± 2
Theoretical yield (m²/l)	UNE 48 282-94	8-9 m2/l (coat of 50 micras)
Supply viscosity	UNE-EN ISO 2431	90±5 K.U. at 20¼C
COVS RD 117/2003 (Suministro) (Instalaciones)	UNE EN ISO 11890	1.176%

Application Instructions

Application equipment	Brush, roll or spray gun, conventional airless sprayer.
Spray nozzle	
Application solvent:	Water
Recommended coat thickness:	80-100 gr/m²

Drying / Polymerisation

Touch dry	60 a 90 minutes (depending on thickness and temperature)
Hard dry	2 - 3 hours, depending on thickness applied and ambient conditions
Total dry	4 - 6 hours, depending on thickness applied and ambient conditions

Remarks

See general conditions
In air-dried water-soluble line products the atmospheric conditions of temperature and relative humidity are important, ideally 20ºC and 65% R.H.
Apply the product when use and curing is at temperatures over 10ºC.
Stir thoroughly before use before use.
It is important to ventilate well during application on closed surfaces and subsequent polymerisation
Do not store opened or started containers.

Oficinas centrales / Headquarters / Siège social
San Fernando, 116. D.P. 26300 Nájera. La Rioja. Spain
Tel. (34) 941 410 000 / Fax (34) 941 410 111 / www.barpimo.com

Do not store at below 5ºC
For toxicological standards, consult FICHA DE SEGURIDAD.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 11-03-2021 This sheet replaces all previous versions.

***Oficinas centrales** / Headquarters / Siège social*
San Fernando, 116. D.P. 26300 Nájera. La Rioja. Spain
Tel. (34) 941 410 000 / Fax (34) 941 410 111 / www.barpimo.com