BARNIZ MARINO

EXTERIORES

RESISTENTE A LA INTEMPERIE

COVS

Product Description Varnish marine and high quality based on alkyd resins modified with urethanes



Technical Characteristics

Colour	Colourless
Appearance	Gloss and satin
Touch-dry	5-7 hours, depending on the type of wood and atmospheric conditions
Repainting	After 24 hours
Yield	17 - 20 m²/l, coat, depending on conditions of surface
Thinner	DILUYENTE SINTETICOS Y GRASOS 250
Storage	Excellent up to 1 year in original container, under normal temperature and humidity conditions.

Properties

Easy to apply and spread, with good penetration into the wood.
Filling power
Resistant to the wood expanding and contracting
Finish with balanced hardness and elasticity and elastic
Resistant to the outdoors

Applications

Suitable for protection and decoracion de on surfaces on boats, wooden buildings near the sea, indoors and and outdoors:.
Suitable for finish and decoracion de of wooden surfaces outdoors, doors, windows and wooden facings..., where BARPIDECOR protective treatment has been applied.

Method of Use

Stir the contents of the pot well
Apply in thin, even, well-spread coats
A round brush and spray gun: adjust viscosity with DILUYENTE SINTETICOS Y GRASOS 250

Preparation of surfaces

On on wood without protector and unvarnished surfaces: Clean, sandpaper and eliminate dust, grease, oil, wax, small imperfections, etc.
On on worn, previously varnished or painted wood surfaces: Eliminate these layers and proceed as before
Apply three coats, suitably diluted, lightly sand between coats to facilitate absorption and improve the finish
On barpidecor protector surfaces: Apply one or two coats, depending on the application of the protector

Other data

Packaging	0.375L, 0.750L, 4L, 20L
VOCS GR/L	441

Remarks

Oficinas centrales */ Headquarters / Siège social*
San Fernando, 116. D.P. 26300 Nájera. La Rioja. Spain
Tel. (34) 941 410 000 / Fax (34) 941 410 111 / www.barpimo.com

Shake contents of containers before use.
For toxicological standards, consult FICHA DE SEGURIDAD.
Do not store opened or started containers.
Apply with good air renewal.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 07-11-2013 This sheet replaces all previous versions.

Oficinas centrales */ Headquarters / Siège social*
San Fernando, 116. D.P. 26300 Nájera. La Rioja. Spain
Tel. (34) 941 410 000 / Fax (34) 941 410 111 / www.barpimo.com