Reference: A2726

BARNIZ IGNIFUGO ECOBARP AL AGUA SATINADO

Product Description	Water-based flame retardant varnish, based on special resins. Resistant to direct fire action and flame.
Certificates	Reaction to fire UNE-EN 13501-1 classified as B-s 1, d 0



Technical Characteristics

Colour	Colourless
Appearance	Satin
Touch-dry	30-60 minutes, depending on the type of wood and the atmospheric conditions
Repainting	After 4-8 hours
Yield	11-14 m²/ l per coat, depending on the state and type of surface
Thinner	Water
Storage	Excellent up to 1 year in original container, under normal temperature and humidity conditions.

Properties

Easy to apply
High protection.
Maximum yield
High-solid
Repels water and ambient humidity and regulates transpiration of wood thereby avoiding warping
Resistant to the outdoors and to solar radiation
Maximum hardness
Decorates and heightens the wood's natural beauty

Applications

Suitable for finish and protection on indoor and outdoor surfaces, windows, doors, beams, beams and ceilings.

Method of Use

Stir the contents of the pot well
Apply in thin, even, well-spread coats
A round brush and roller: as supplied in the container or slightly diluted with water.

Preparation of surfaces

On unprotected surfaces: Clean, sandpaper and eliminate dust, grease, oil, wax, small imperfections, etc.
On treated with protective products which have become deteriorated surfaces: Sandpaper and eliminate dust
On with old or deteriorated varnish surfaces: Eliminate these layers and proceed as before
Apply barpidecor Fondo primer as a complement to the treatment.
For toning new woods or increase resistance to outdoor conditions, apply subsequent coats of Water-based Barpidecor of the colour chosen until the desired tone is achieved, and finish applying one or two coats of WATER-BASED FLAME RETARDANT VARNISH.
On tropical woods, apply a coat of Tropical Woods Insulating Sealant previously
Apply 2-3 coats depending on the exposure and atmospheric conditions
Dilute the first coats slightly with water and sand gently between coats.
Sobre maderas tropicales aplicar previamente, dependiendo del tipo de madera, 1-2 manos de Sellador Aislante Madera Tropicales. Ref. I6860

Other data

Packaging	0.375L, 0.750L, 4L

Oficinas centrales */ Headquarters / Siège social*
San Fernando, 116. D.P. 26300 Nájera. La Rioja. Spain
Tel. (34) 941 410 000 / Fax (34) 941 410 111 / www.barpimo.com

VOCS GR/L	48 g/lt.

Remarks

Application not advisable for wood with high moisture content, above 20%.
Shake contents of containers before use.
For toxicological standards, consult FICHA DE SEGURIDAD.
Do not store opened or started containers.
Apply with good air renewal.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 25-05-2018 This sheet replaces all previous versions.

Oficinas centrales */ Headquarters / Siège social*
San Fernando, 116. D.P. 26300 Nájera. La Rioja. Spain
Tel. (34) 941 410 000 / Fax (34) 941 410 111 / www.barpimo.com