Issued 03/25

DULUX AQUAMAX HIGH GLOSS

Dulux AquaMax High Glossisa durable gloss finish, specially formulated for use on interior and exterior wood and metal. With excellent coverage and effortless application,Dulux AquaMax High Gloss formulation is water based, quick drying, low odour, non-yellowing and recoatable after 5-6 hours (in standard drying conditions) to a smooth flawless finish.

KEY BENEFITS

- Excellent Gloss Finish
- Interior / Exterior use
- Quick Drying: 1-2 hours touch dry
- Non-yellowing

PRODUCT INFORMATION

Typical Use

Ideal for use on interior and exterior woodwork and primed metal.

Pack Size

750ml, 2.5L, 5L

Colour Range

Pure Brilliant White

Practical Coverage

A guide to the practical coverage which can be achieved under normal conditions is up to 18m² per litre.

Film Thickness

Dependent on the coverage achieved.
Wet: 80-100 microns. Dry: 32-40 microns

Composition (nominal)

Pigment: Lightfast Pigments.Binder: Adhesion-promoted Acrylic Copolymer Emulsion.
Solvent: Water.

Volume Solids: 37% (nominal).

Sheen Level:

Gloss 65-70%% under standard conditions.
For more information seeDuluxTrade.ie.

SURFACE PREPARATION

To get the best results, ensure surfaces to be painted are sound, clean, and dry (new surfaces particularly must be fully dry). Remove all loose and defective coatings, if necessary, stripping back to bare wood. Special precautions should be taken during surface preparation of pre-1990s paint surfaces over wood and metal as they may contain harmful lead.

Exterior: Remove and treat any mould, algae, lichen, or moss with Weathershield Fungicidal Wash*. Remove defective glazing material, clean the rebates and any loose or open joints. Replace any rotten wood and troublesome knots with new timber.

Thoroughly rub down previously painted surfaces, using ‘wet flatting’ methods where possible, then wipe off with a damp, lint free cloth. Apply 1 or 2 coats of an appropriate knotting solution to treat any remaining knots in wood. Any surface defects should be filled with the appropriatePolycell product.

Prime then Undercoat all new or bare wood with 2 coats ofDulux AquaMax Primer Undercoat White.

Fill any surface defects, open joints etc. and replace any missing glazing material. New joinery is often factory primed using a satin basecoat (also called a

Issued 03/25

DULUX AQUAMAX HIGH GLOSS

dual-purpose primer). These materials quickly erode when left exposed and may need to be re-primed.

Prime any new bare metal with appropriateDulux Trade Metalshield Primer. Then undercoat with Dulux AquaMax Primer Undercoat White or Dulux AquaMax Undercoat Colour Mixing depending on the colour of the topcoat.

SYSTEMS INFORMATION

STIR THOROUGHLY BEFORE USE. Apply 2 coats ofDulux AquaMax High Gloss allowing 5-6 hours between coats. Where a strong colour change is involved, an extra coat may be required.

APPLICATION METHOD

Brush or Roller. Do not use in temperatures below 7ºC or outside where there is a likelihood of rain, fog or frost.

FURTHER SUPPORT

Thinning

Thinning is not usually necessary, but if required add up to 1-part clean water to 20 parts paint.

Drying Times

Single coat at standard thickness:

Touch Dry: 1-2 hours.

Recoat:5-6 hours

Responsible Cleaning

Cleaning After Final Use:Cleaning your brushes and rollers immediately after their final use ensures they can be reused for multiple projects, saving you money and reducing waste.

Cleaning:

1. Remove ExcessPaint: Scrape off excess paint into container for future projects.
2. Clean with Warm, Soapy Water:Use warm, soapy water in a sealed container, such as a bucket or empty tub, to clean your brushes and rollers.
3. Rinse Thoroughly:Ensure all soap and paint residues are completely rinsed out into container.
4. Dry Naturally:Allow brushes and rollers to dry naturally and store them in a dry, dust- free place.
5. Allowing solids to settle:Allow the paint solids to settle at the bottom of the container. Once settled, pour the clear water into another container for reuse or dispo sal.
6. Responsible Disposal:Let the remaining paint solids dry out completely and dispose of them as solid waste.

Transportation & Storage

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

Storing & Responsible Disposal

1. Reuse, Recycle,orDonate: Whenever possible, reuse, recycle, or donate leftover paint. Find local services at mywaste.ie or consider advertising the paint locally. Many good causes often need paint, and a little can go a long way in brightening up community spaces!

2.Dispose Responsibly:Never pour paint or wastewater down drains or sinks. Dispose of them responsibly. Follow the instructions at mywaste.ie to recycle empty packs

Issued 03/25

DULUX AQUAMAX HIGH GLOSS

3.Reuse Roller Cages:Roller cages can be reused. Simply remove the sleeve and store the cage in a dry, dust-free place.

4.Dispose of Unusable Brushes and Sleeves:If your brush or roller sleeve cannot be cleaned or reused, place it in your general waste bin. While recycling is important, bristles or roller sleeves with paint can cause issues at recycling canters, so it's best to dispose of them correctly.

Guidance for Disposing of Paint Wash Water

1. Contain wash-water: Always use a bucket or container to collect all the wash water when cleaning paint brushes and rollers. Avoid letting the wash water run directly into drains, sinks, or onto the ground.
2. Allowing solids to settle:Allow the paint solids to settle at the bottom of the container. Once settled, pour the clear water into another container for reuse or disposal.
3. Responsible Disposal:Let the remaining paint solids dry out completely and dispose of them as solid waste.

VOC

EU limit value for this product (cat.: A/d): 130g/l (2010). This product contains max. 45g/l VOC.
VOC Content: Low (0.30 – 7.99%)

If you need further support, please contact the Dulux Technical Advice Centre on +353 1 455 6099

* Weathershield Fungicidal Wash contains: DDAC

Always read full Health, Safety & Environmental Information on can before use.

Safety datasheet is available free on request by telephoning theDulux Technical Advice Centre or by visiting dulux.ie

AkzoNobel, the AkzoNobel logo, Dulux, the Flourish logo, Dulux Trade, Weathershield, Mouldshield, Polycell, Polyfilla, Community RePaint and the Planet Possible logo are trademarks of the AkzoNobel group. © AkzoNobel 2025