TECHNICAL DATA SHEET
COLORCAN MARINE ANTI-SLIP DECK PAINT

WWW.VINNYBYRNE.COM

PART NO. COLORCAN/MARINE

DESCRIPTION

COLORCAN MARINE ANTI-SLIP DECK PAINT IS A ONE PACK POLYURETHANE, NON-SLIP FINISH FOR DECKS & OTHER HORIZONTAL SURFACES. CONTAINING A TOUGH POLYURETHANE RESIN, IT PROTECTS AGAINST EVERY DAY WEAR & TEAR.



PROPERTIES

- ANTI-CORROSIVE & UV RESISTANT
- SPECIALLY DEVELOPED FOR EXTREME WEATHER CONDITIONS
- EXCELLENT WEAR RESISTANCE
- SATIN FINISH LIMITS GLARE & ACCUMULATION OF DIRT
- EASILY CLEANED



BASIC USES

- INTERIOR & EXTERIOR - ABOVE THE WATERLINE
- GELCOAT, NEW & RUSTED METAL, ALUMINIUM, WOOD...
- PREVIOUSLY PAINTED SURFACES - POLYURETHANE, EPOXY, ALKYD, ACRYLIC
- DECKS, RAMPS, STEPS



APPLICATION TOOLS

- BRUSH
- ROLLER - MOHAIR / SHORT PILE
- NOT SUITABLE FOR SPRAY APPLICATION

TECHNICAL DATA SHEET
COLORCAN MARINE ANTI-SLIP DECK PAINT

TECHNICAL INFORMATION	
FINISH	SATIN
BINDER	URETHANE ALKYD
SHELF LIFE	1 YEAR (UNOPENED)
FLASH POINT	<60°C
SIZE	1L
COLOUR	ANY
WET FILM THICKNESS	150µM
DRY FILM THICKNESS	120µM
STORAGE**	ORIGINAL CONTAINER
COVERAGE*	9M2 TO 10M2 PER L
CLEAN UP	WHITE SPIRIT





*ACTUAL COVERAGE WILL VARY DEPENDING ON APPLICATION METHOD, TEXTURE, AGE & POROSITY OF SURFACE

**KEEP FROM FREEZING & HIGH TEMPERATURES



TECHNICAL DATA SHEET
COLORCAN MARINE ANTI-SLIP DECK PAINT

SURFACE PREPARATION*

SURFACE MUST BE CLEAN, DRY & FREE OF OIL, GREASE, SALT & OTHER SURFACE CONTAMINATION INCLUDING ANY PREPARATION RESIDUE.

UNCOATED WOODEN SURFACES

NEW & WEATHERED (12 MONTHS+):

- ABRADE SURFACE WITH 80 GRIT ABRASIVE
- THOROUGHLY DUST OFF
- WIPE SURFACE WITH A CLOTH SOAKED IN ACETONE OR SIMILAR (NOT WHITE SPIRITS).
- ALLOW TO FLASH OFF

NEW METAL (NOT ALUMINIUM)

- CLEAN SURFACE WITH SUITABLE CLEANING SOLVENT
- BLAST (SA2 1/2), GRIND (P24-P36) OR SAND (40-120 GRIT) SURFACE.
- CLEAN SURFACE OF ALL PREPERATION RESIDUE

PAINTED SURFACES (WOOD, METAL, GELCOAT)

COATING IN GOOD CONDITION & WELL ADHERED:

- CLEAN SURFACE WITH SUITABLE CLEANING SOLVENT
- RINSE THOROUGHLY & ALLOW TO DRY
- ABRADE SURFACE WITH 80-100 GRIT ABRASIVE
- CLEAN SURFACE OF ALL RESIDUE

COATING IN POOR CONDITION & POORLY ADHERED:

- CLEAN SURFACE WITH SUITABLE CLEANING SOLVENT
- REMOVE EXISTING COATING BACK TO UNIFORM, BRIGHT, BARE CLEAN MERTAL SURFACE BY BLASTING (SA2 1/2), GRINDING (P24-P36), SANDING (40-120 GRIT)
- CLEAN SURFACE OF ALL RESIDUE

*SURFACE PREPERATION CONTINUES ON FOLLOWING PAGE



TECHNICAL DATA SHEET
COLORCAN MARINE ANTI-SLIP DECK PAINT

WWW.VINNYBYRNE.COM

PART NO. COLORCAN/MARINE

ALUMINIUM

- CLEAN SURFACE WITH A SUITABLE CLEANING SOLVENT
- BLAST SURFACE OR SAND WITH 24-120 GRIT ABRASIVE
- CLEAN SURFACE OF ALL PREPERATION RESIDUE

GELCOAT

- REMOVE ALL TRACES OF SILICONE, WAX, PARAFFIN ETC. WITH ACETONE
- CLEAN SURFACE WITH HOT SOAPY WATER
- RINSE THOROUGHLY & ALLOW TO DRY
- SAND WITH 180-220 GRIT
- CLEAN SURFACE OF ALL PREPERATION RESIDUE

RUSTED METAL SURFACES

LIGHT OR MODERATE RUST:

- REMOVE ALL LOOSE & FLAKY RUST BACK TO A SOUND SURFACE
- REMOVAL OF FIRM RUST IS NOT REQUIRED
- CLEAN SURFACE WITH SUITABLE CLEANING SOLVENT

HEAVY OR SEVERE RUST:

- CLEAN SURFACE WITH SUITABLE CLEANING SOLVENT
- REMOVE ALL RUST BACK TO A UNIFORM, BRIGHT, CLEAN, BARE METAL SURFACE BY BLASTING (SA2 1/2), GRINDING (P24-P36), SANDING (40-120 GRIT)

APPLICATION

- STIR POT WELL (2-3 MNS) BEFORE & DURING APPLICATION. DO NOT THIN.
- DUST DRY - 3 HOURS
- TOUCH DRY - 6 HOURS
- RECOAT - 12 HOURS
- DRYING TIMES SHOULD BE ADJUSTED ACCORDING TO THE CONDITIONS E.G. TEMPERATURE & HUMIDITY

WESTLINK - NAAS RD
T: 01 626 1700
E: SALES@VINNYBYRNE.COM

SANTRY - BESIDE AIRPORT
T: 01 842 8501
E: RAY@VINNYBYRNE.COM

REFER TO SAFETY DATA SHEET (MSDS) OR MORE INFORMATION AT WWW.VINNYBYRNE.COM

10/03/2025