

AQUABARP EXTERIOR WAX BV



Product Description

Single component water based coloured transparent stain

Properties

Acrylic nature

Waxy appearance

Strong penetrating power

Good at covering defects.

Good weather resistance

Contains UV filter

Available in a wide range of colours

Low viscosity product

Repels water and ambient humidity and regulates transpiration of wood thereby avoiding warping

Recommended use

Product to use for the open-pore protection of outdoor woodwork and garden furniture

Certificates

Certified by AIDIMA as suitable for outdoor use in accordance with Standard UNE EN 927

Carta de Colores

[Linea de madera Aquabarp](#)

Certificados

[Aquabarp_pino.pdf](#), [Certificado.de.Producto.Simbolo.de.Calidad.AIDIMA, 20150323160950359_0001.pdf](#), [X3eTY_C8C6526.pdf](#)



Technical Characteristics

	Norma	Value
Solids by weight (%)	UNE EN ISO 3251	13+-2%
Viscosity (Ford cup 4)	UNE EN ISO 2431	12"+-2" FORD 4
Density (Kg/L)	UNE EN ISO 2811-1	1.015+/-0.020
VOCs (%)	UNE EN ISO 11890	0.962%
VOCs (gr./lt)	UNE EN ISO 11890	9.818
Colour		Wide range of colours
Appearance		Matt

Mixing Characteristics

Solvent	Water
Percentage dilution	5-10%

Application Characteristics

Application System	Aerographic, airless, airmix, round brush, flow coating and immersion
Application on	Solid wood, garden furniture and windows, doors, beams
Recommended quantity of product	100-120 gr/m ²
Number of coats	1-2
Temperature of Application	>15
Ambient Humidity	Less than 70%
Dry to dust	30 a 40 minutes (depending on thickness and temperature)

Touch-dry

1 - 2 hours, depending on thickness applied and ambient conditions

Total hardening

16 - 24 hours, depending on thickness applied and ambient conditions

Repainted

For second coat after 4 - 6 hours

Remarks re application process

Apply one or two coats, sanding between coats.

The moisture content of the wood to be treated must not exceed 15%

If you wish to shorten drying time, you can force-dry with hot air or use infrared or microwave driers.

It is recommended that the surface is not exposed to the elements until about 7 days have elapsed.

Remarks

Shake contents of containers before use.

In outdoor use, as a water-based product, it is sensitive to the action of rain.

Clean utensils with water immediately after use.

Do not store at below 5°C

For toxicological standards, consult FICHA DE SEGURIDAD.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 28-12-2010 This sheet replaces all previous versions.