

Información de producto | FICHA TÉCNICA

BODY FILLER

250 - 1000 g / 8.82 - 35.27 oz

GENERAL DESCRIPTION

Styrene-free two-component polyester filler specially developed for repairing small irregularities and imperfections in vehicle bodywork.

Its formulation with micro-filler components provides an exceptionally smooth and uniform surface, making bodywork preparation easier before paint application.

It offers very good adhesion to steel, galvanized steel, cast iron, and fiberglass, while also being easy to apply and sand. Its rapid curing allows repairs to be completed efficiently and enables the finishing process to continue within a short time.

INSTRUCTIONS FOR USE

- Prepare the surface so that it is dry, clean, and free from dust, grease, dirt, rust, and poorly adhered paint residues.
- On rusted surfaces, completely remove all rust and then apply MTN WEPRO Metal Epoxy Primer or MTN WEPRO Anti Rust Primer.
- Apply a line of hardener across the entire portion of filler (mixing ratio 100:2). Mix thoroughly until a homogeneous consistency and uniform color are obtained.
- For thick applications, apply in several layers, allowing each layer to fully cure before applying the next.
- Allow to dry for 30 minutes at 20°C. Drying time will depend on ambient temperature. Higher temperatures accelerate curing.
- Sand initially with P80-P120 sandpaper and continue with P180-P240 for finishing. For high-quality finishes, use finer grits.
- Before final finishing, ensure that the repair is completely cured.
- Clean spatulas with MTN WEPRO Solvent Cleaner or a universal cleaning solvent before the product hardens.

PHYSICAL CHARACTERISTICS

Color:	White
Nature:	Styrene-free Unsaturated Polyester
Specific Gravity:	1.6 kg/L at 20°C
VOC:	222 g/L
Working Time After Mixing with Hardener	
	3 min at 30°C
	5 min at 20°C
	11 min at 10°C
Drying Time	
	15-20 min at 30°C
	20- 25 min at 20°C
	30-40 min at 10°C
Sanding Time:	Approximately 30 min
Full Cure	Approximately 2 hours (20°C)
Recommended Sanding:	P80 - P120 - P180 - P240
Safety:	Read the label and Safety Data Sheet before using the product. Comply with applicable safety, occupational hygiene, and waste management regulations.
Cleaning:	Fresh product can be cleaned with acetone, alcohol, or universal thinner. Once cured, remove mechanically.
Storage:	Store in its original tightly closed container in a cool, dry, and well-ventilated area, protected from moisture and direct sunlight, at temperatures between +5°C and +30°C.
Shelf Life:	1.5 years in the original unopened container.

230726

FEATURES

- Styrene-free..
- 2K polyester filler
- Specially designed for bodywork repairs.
- Ideal for fine filling of small irregularities and imperfections.
- Very good adhesion.
- Easy to apply.
- Easy to sand.
- Fast curing.
- Can be overpainted with any type of paint.
- White color.

APPLICATIONS

Ideal for:

- Vehicle bodywork repair.
- Repair of small dents and irregularities.
- Filling minor surface imperfections.
- Smoothing and leveling previously repaired surfaces.
- Surface preparation prior to painting.
- Repair and finishing of automotive components.
- Professional bodywork and repair applications.

Can be applied to:

- Steel.
- Galvanized steel.
- Cast iron
- Fiberglass.

Substrates must be properly prepared and free from mold-release agents. Once cured and sanded, the repaired surface can be overcoated with any type of paint.

IMAGE



Dimensions

(250 g): Height 76 mm, Diameter 96.5 mm . 1000 g: Height 130 mm, Diameter 99 mm.

LABEL



COD. BARRAS/BAR CODE

Masilla para Carrocería / Body Filler 250 g
SPMA0101006

Masilla para Carrocería / Body Filler 1000g
SPMA0101011

